

TEST REPORT


<u>APPLICANT</u>	: HANGZHOU XINGUANG BICYCLE INDUSTRY CO., LTD
<u>ADDRESS</u>	: JIAOSHAN VILLAGE, YIQIAO TOWN, XIAOSHAN DISTRICT, HANGZHOU CITY, ZHEJIANG PROVINCE, CHINA
<u>SAMPLE DESCRIPTION</u>	: FOOT SCOOTER
<u>ITEM NO.</u>	: 371-017BU, 371-017WT, 371-019BK, 371-019BU, 371- 020BU, 371-020GN, 371-020OG, 371-021BK, 371- 021BU, 371-021WT
<u>AGE REQUESTED ON APPLICATION FORM</u>	: 3+
<u>LABELED AGE GRADE</u>	: 3+
<u>AGE GRADE APPLIED IN TESTING</u>	: 3+
<u>SAMPLE RECEIVED DATE</u>	: 28-Apr-2020
<u>FURTHER INFORMATION DATE</u>	: 15-May-2020
<u>TURN AROUND TIME</u>	: 28-Apr-2020 to 15-May-2020

The following test item(s) was/were performed on selected sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Mechanical and Physical Properties	ASTM F963-17	Pass
Flammability of Toys	ASTM F963-17	Pass
Heavy Metals	ASTM F963-17	Pass
Total Lead Content in Paint / Surface Coating	US CPSIA, Section 101	Pass
Total Lead Content in Substrate	US CPSIA, Section 101	Pass
Phthalates Content	US CPSIA, Section 108	Pass
Phthalates Content	CPSC 16 CFR part 1307	Pass

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****


Signed for and on behalf of
Eurofins Product Testing Service (Shanghai) Co., Ltd. Hangzhou Branch



Sara Liu
Lab Manager

Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to info.hz@eurofins.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to china.complaint@eurofins.com and

SAMPLE PHOTO(S)



EFHZ20042702-CG-02

TO BE CONTINUED

REFERENCE SAMPLE PHOTO



The reference samples have not been tested in current report, but according to customer's request, the pictures have also been included. For sample tested in current report, please refer to "Sample photo(s)".

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Sample No.
1	Blue coating	E
2	Green coating	E
3	Orange coating	E
4	Black coating	E
5	Dark blue coating	E
6	Blue coating on metal	A B C
7	Black coating on metal	A B C D
8	Green coating on metal	D
9	Colorful coating on soft plastic(steering bar)	C D
10	White foam(steering bar)	C D
11	Silver flashy soft plastic wire sheath	B C
12	Transparent soft plastic sheet excluding coating(steering bar)	C D
13	Black soft plastic(brake wire)	B C D
14	Black soft plastic wheel	A B C D
15	Black soft plastic wire sheath	A D
16	Black soft plastic brake gasket	A B C D
17	Black soft plastic(nozzle)	A B C D
18	Colorful soft plastic sticker	A
19	Transparent/black soft plastic sticker	B C D
20	Black plastic handle	A B C D
21	Black plastic(brake component)	A B C D
22	Black plastic deck	A B C D
23	Black plastic pad	A B C D
24	Black plastic knob(nozzle)	A B C D
25	White plastic Velcro hook(steering bar)	C D
26	White fabric Velcro loop(steering bar)	C D
27	Steel blue plated metal screw/nut(handle)	A B C D
28	Bright silver metal screw/nut	A B C D
29	Silver metal(brake component)	A B C D
30	Silver metal excluding coating(body)	A B C D
31	Silver metal hub	A B C D
32	Silver metal spoke	A B C D
33	Silver metal axle	A B C D
34	Silver metal brake gasket	A B C D
35	Silver metal spring(stander)	A B C D
36	Silver metal stander	A B C D
37	Golden plated metal nozzle	A B C D

TO BE CONTINUED

TEST RESULT

Mechanical and Physical Properties

Test Request: As specified in Consumer Safety Specification ASTM F963-17

Section	Description	Result
4.1	Material Quality	P
4.3.7	Stuffing Materials	N/A
4.5	Sound-Producing Toys	N/A
4.6	Small Objects	P
4.6.1	Toys that are intended for children under 36 months of age	N/A
4.6.2	Mouth-Actuated Toys	N/A
4.6.3	Toys that are intended for children over 36 months but less than 72 months	P
4.7	Accessible Edges	P
4.8	Projections	P
4.8.1	Bath Toy Projections	N/A
4.9	Accessible Points	P
4.10	Wires or Rods	P
4.11	Nails and Fasteners	P
4.12	Plastic Film	N/A
4.13	Folding Mechanisms and Hinges	N/A
4.14	Cords, Straps and Elastics	N/A
4.15	Stability and Over-Load Requirements	P
4.16	Confined Spaces	N/A
4.17	Wheels, Tires, and Axles	P
4.18	Holes, Clearances, and Accessibility of Mechanisms	P
4.19	Simulated Protective Devices	N/A
4.20	Pacifiers	N/A
4.21	Projectile Toys	N/A
4.22	Teethers and Teething Toys	N/A
4.23	Rattles	N/A
4.24	Squeeze Toys	N/A
4.25	Battery-Operated Toys (exclude section 4.25.10 Battery-powered ride-on toys and section 4.25.11 Toys contain secondary cells or secondary batteries)	N/A
4.26	Toys Intended to be Attached to a Crib or Playpen	N/A
4.27	Stuffed and Beanbag-Type Toys	N/A
4.28	Stroller and Carriage Toys	N/A
4.30	Toy Gun Marking	N/A
4.31	Balloons	N/A
4.32	Certain Toys with Nearly Spherical Ends	N/A
4.33	Marbles	N/A
4.34	Balls	N/A
4.35	Pompoms	N/A
4.36	Hemispheric-Shaped Objects	N/A
4.37	Yo Yo Elastic Tether Toys	N/A
4.38	Magnets	N/A
4.39	Jaw Entrapment in Handles and Steering Wheels	N/A
4.40	Expanding material	N/A
4.41	Toy Chests	N/A
5	Labeling Requirements	
5.2	Age Grading Labeling	P
5.3	Safety Labeling Requirements	P

TEST RESULT

Section	Description	Result
5.4	Aquatic Toys	N/A
5.5	Crib and Playpen Toys	N/A
5.6	Mobiles	N/A
5.7	Stroller and Carriage Toys	N/A
5.8	Toys Intended to be Assembled by an Adult	P
5.9	Simulated Protective Devices	N/A
5.10	Toys with Functional Sharp Edges and Sharp Points	N/A
5.11	Small Objects, Small Balls, Marbles and Balloons (16 CFR 1500.19)	P
5.12	Toy Caps (16 CFR 1500.86 for Required Labeling)	N/A
5.13	Art Materials (16 CFR 1500.14(b)(8))	N/A
5.14	Electric Toys	N/A
5.15	Battery-Operated Toys	N/A
5.15.1	Battery-Powered Ride-On Toys	N/A
5.15.2	Button or Coin Cell Batteries	N/A
5.16	Promotional Materials	P
5.17	Magnets	N/A
6	Instructional Literature	
6.1	Definition and Description	P
6.2	Crib and Playpen Toys	N/A
6.3	Mobiles	N/A
6.4	Toys Intended to be Assembled by an Adult	N/A
6.5	Battery-Operated Toys	N/A
6.6	Battery-Powered Ride-On Toys	N/A
6.7	Toys in Contact with Food	N/A
6.8	Toy Chests	N/A
7	Producer's Markings	
7.1	Producer's or Distributor's Name and Address	P
7.2	Battery-Powered Ride-on Toys	N/A
7.3	Toy Chests	N/A

Remark:

P – Pass

N/A – Not Applicable

Flammability of Toys

Test Request: As specified in ASTM F963-17, Section 4.2, testing procedure for materials other than textiles (excluding paper) used in toys is contained in Annex A5.

Sample	Limit	Result
A ~ D	0.1 inch/second	DNI

Remark:

DNI – Did Not Ignite

TO BE CONTINUED

TEST RESULT

Heavy Metals

1) ASTM F963-17- Heavy Elements – Total Lead in Paint and Similar Surface-Coating Material(Clause 4.3.5.1(1))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result			
				6	7	8	9
Total Lead	mg/kg	90	10	ND	18	ND	ND

2) ASTM F963-17- Heavy Elements – Total Lead in Substrate Material (Clause 4.3.5.2(2)(a))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result					
				10	11	12	13	14	15
Total Lead	mg/kg	100	10	ND	595*	ND	1265*	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				16	17	18	19	20
Total Lead	mg/kg	100	10	14	22	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				21	22	23	24	25
Total Lead	mg/kg	100	10	46	ND	54	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result			
				27	28	29	30
Total Lead	mg/kg	100	10	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				31	32	33	34	35
Total Lead	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result	
				36	37
Total Lead	mg/kg	100	10	ND	31045*

TO BE CONTINUED

TEST RESULT

3) ASTM F963-17- Heavy Elements – Total Elements Content, Initial Screening for Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay(Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Antimony	mg/kg	60	5	ND	62*	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	ND	146	ND	489	32
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				6	7	8	9	10
Total Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	3695*	ND	10928*	ND	46
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	39	ND	ND	ND
Total Lead	mg/kg	90	10	ND	18	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				11	12	13	14	15
Total Antimony	mg/kg	60	5	ND	ND	110*	23	26
Total Arsenic	mg/kg	25	5	ND	ND	ND	43	ND
Total Barium	mg/kg	1000	10	334	1698*	223	ND	116
Total Cadmium	mg/kg	75	5	366*	ND	46	ND	26
Total Chromium	mg/kg	60	5	14	ND	14	ND	ND
Total Lead	mg/kg	90	10	595*	ND	1265*	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				16	17	18	19	20
Total Antimony	mg/kg	60	5	54	ND	83*	47	621*
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	14	22	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result				
				21	22	23	24	25
Total Antimony	mg/kg	60	5	783*	ND	ND	ND	137*
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	344	ND	ND	196	ND
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	12	ND	15	ND	ND
Total Lead	mg/kg	90	10	46	ND	54	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				26				
Total Antimony	mg/kg	60	5	143*				
Total Arsenic	mg/kg	25	5	ND				
Total Barium	mg/kg	1000	10	ND				
Total Cadmium	mg/kg	75	5	ND				
Total Chromium	mg/kg	60	5	ND				
Total Lead	mg/kg	90	10	ND				
Total Mercury	mg/kg	60	5	ND				
Total Selenium	mg/kg	500	10	ND				

4) ASTM F963-17- Heavy Elements – Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay (Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.2 to 8.3.5 (excluding 8.3.5.5(3))

Tested Item(s)	Unit	Limit	MDL	Result				
				2	6	8	11	12
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	341	312	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				13	18	20	21	25
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result
				26
Soluble Antimony	mg/kg	60	5	ND
Soluble Arsenic	mg/kg	25	5	ND
Soluble Barium	mg/kg	1000	10	ND
Soluble Cadmium	mg/kg	75	5	ND
Soluble Chromium	mg/kg	60	5	ND
Soluble Lead	mg/kg	90	10	ND
Soluble Mercury	mg/kg	60	5	ND
Soluble Selenium	mg/kg	500	10	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

The analytical results were adjusted by subtracting analytical correction factor.

* On the initial analysis for soluble heavy metals content, any tested component of greater than the set limit, the result is inconclusive for the requirement and therefore were retested with soluble heavy metals analysis of ASTM F963-17, Sections 8.3.2 to 8.3.5 as specified in Section 8.3.1.3. The result herein is for reference only (show data), please refer to soluble heavy metals content analysis for the corresponding conclusive results.

TO BE CONTINUED

TEST RESULT

Total Lead Content in Paint / Surface Coating

Test Request: Total lead in paint/ similar surface coatings as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1003-09.1
The sample was acid digested, and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result			
				1+2+3	4+5	6+7+8	9
Total Lead(Pb)	mg/kg	90	10	ND	ND	ND	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

TO BE CONTINUED

TEST RESULT

Total Lead Content in Substrate

Test Request: Total lead in substrate as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1001-08.3, CPSC-CH-E1002-08.3
The sample was acid digested, and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result	
				10	15+16+17
Total Lead(Pb)	mg/kg	100	10	ND	12

Tested Item(s)	Unit	Limit	MDL	Result			
				18	19	20+21+22	23+24+25
Total Lead(Pb)	mg/kg	100	10	ND	ND	15	18

Tested Item(s)	Unit	Limit	MDL	Result			
				27	28+29+30	31+32+33	34+35+36
Total Lead(Pb)	mg/kg	100	10	ND	ND	ND	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 108

Test Method: CPSC-CH-C1001-09.3

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					1+2+3	4+5	6+7+8
For toys and childcare articles							
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Additional requirements for toys and childcare articles, which can be placed in the mouth by children							
Diisononyl phthalate (DINP)	68515-48-0	%	0.1	0.005	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Di-iso-decylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result	
					10	18
For toys and childcare articles						
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	0.016	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND
Additional requirements for toys and childcare articles, which can be placed in the mouth by children						
Diisononyl phthalate (DINP)	68515-48-0	%	0.1	0.005	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND
Di-iso-decylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result	
					19	23+24+25
For toys and childcare articles						
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	0.024
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND
Additional requirements for toys and childcare articles, which can be placed in the mouth by children						
Diisononyl phthalate (DINP)	68515-48-0	%	0.1	0.005	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND
Di-iso-decylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates as specified in CPSC 16 CFR part 1307.

Test Method: CPSC-CH-C1001-09.4

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					1+2+3	4+5	6+7+8
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result	
					10	18
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	0.016	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result	
					19	23+24+25
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	0.024
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

As per client's request, only the appointed materials have been tested.

END OF THE REPORT