

TEST REPORT

APPLICANT : HANGZHOU XINGUANG BICYCLE INDUSTRY CO.,LTD

ADDRESS : JIAOSHAN VILLAGE,YIQIAO TOWN,XIAOSHAN
DISTRICT,HANGZHOU CITY, ZHEJIANG
PROVINCE,CHINA

SAMPLE DESCRIPTION : FOOT SCOOTER

ITEM NO. : 371-029

AGE REQUESTED ON APPLICATION FORM : 3+

SAMPLE RECEIVED DATE : 04-Mar-2024

TURN AROUND TIME : 04-Mar-2024 to 11-Mar-2024

The following test item(s) was/were performed on selected sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Phthalates Content	REACH Annex XVII, Entry 51 & 52	Pass
Polycyclic Aromatic Hydrocarbons (PAHs)	German GS Specification: AfPS GS 2019:01 PAK	Pass
Total Cadmium Content	REACH Annex XVII, Entry 23	Pass

Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Hangzhou) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. Unless otherwise stated from the customer, regulation or the standard specification, Eurofins will consider the measurement uncertainty as calculated by our laboratory and apply according to ILAC G8:09/2019-(binary acceptance base on guard band). If you happen to have any comments, please do it by sending email to info.hz@cpt.eurofinscn.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Hangzhou) Co., Ltd. If you happen to have any complaints, please do it by sending email to chinacomplaint.hz@cpt.eurofinscn.com and referring to this report number.



***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins Product Testing Service (Hangzhou) Co., Ltd

Sara Liu

Sara Liu
Quality Manager



SAMPLE PHOTO(S)



EFHZ24030325-CG-01

TO BE CONTINUED

REFERENCE SAMPLE PHOTO(S)



The reference samples have not been tested in current report, but according to customer's request, the picture has also been included. For sample tested in current report, please refer to "sample photo".

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Sample No.
1	Yellow coating on metal	A

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates content as specified in entry 51&52 of annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Commission Regulation (EU) 2018/2005.

Test Method: EPA 3550C:2007, EPA 8270E:2018, solvent extraction and quantification by GC-MS.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					1
Dibutylphthalate (DBP)	84-74-2	%	-	0.005	ND
Benzyl butyl phthalate (BBP)	85-68-7	%	-	0.005	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	-	0.005	ND
Di-isobutyl phthalate (DiBP)	84-69-5	%	-	0.005	ND
Sum of (DEHP+DBP+BBP+DiBP)	-	%	0.1	-	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	-	0.005	ND
Diisononyl phthalate (DINP)	28553-12-0	%	-	0.005	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	-	0.005	ND
Sum (DNOP + DINP + DIDP)	-	%	0.1	-	ND

Remarks:

As per client's request, only the appointed materials have been tested.

1 mg/kg = 1 ppm = 0.0001%

MDL = method detection limit

ND = Not detected, less than MDL

“- “ = Not Regulated

TO BE CONTINUED

TEST RESULT

Polycyclic Aromatic Hydrocarbons (PAHs)

Test Request: Polycyclic Aromatic Hydrocarbons (PAHs) content according to German GS
Specification: AfPS GS 2019:01 PAK

Test Method: Solvent extraction and quantification by gas chromatography-mass selective detection
(GC-MS) with respect to AfPS GS 2019:01 PAK

Parameter	CAS No.	Unit	Result
			1
PAHs Category			Category 3a
Benzo(a)pyrene	50-32-8	mg/kg	ND
Benzo(e)pyrene	192-97-2	mg/kg	ND
Benzo(a)anthracene	56-55-3	mg/kg	ND
Benzo(b)fluoranthene	205-99-2	mg/kg	ND
Benzo(j)fluoranthene	205-82-3	mg/kg	ND
Benzo(k)fluoranthene	207-08-9	mg/kg	ND
Chrysene	218-01-9	mg/kg	ND
Dibenzo(a,h)anthracene	53-70-3	mg/kg	ND
Benzo(ghi)perylene	191-24-2	mg/kg	ND
Indeno(1,2,3-cd)pyrene	193-39-5	mg/kg	ND
Phenanthrene	85-01-8	mg/kg	ND
Anthracene	120-12-7	mg/kg	ND
Fluoranthene	206-44-0	mg/kg	ND
Pyrene	129-00-0	mg/kg	ND
Naphthalene	91-20-3	mg/kg	ND
Sum of 4 GS PAHS (Phenanthrene, Pyrene, Anthracene, Fluoranthene)	-	mg/kg	ND
Sum of 15 GS PAHs	-	mg/kg	ND

Note:

As per client's request, only the appointed materials have been tested.

mg/kg = milligram per kilogram

ND = not detected, less than 0.2 mg/kg

TO BE CONTINUED

TEST RESULT

Table 1

AfPS GS 2019:01 PAK requirement:

Parameter	Unit	Category 1 Materials intended to be taken into the mouth, or materials in toys acc. to DIR 2009/48/EC or materials in articles intended for the use by children up to 3 years of age having long-term skin contact (more than 30s) within intended use	Category 2 Materials that do not fall into category 1, with long-term skin contact (more than 30s) or repeated short-term skin contact within intended or foreseeable use		Category 3 Materials that do neither fall into category 1 nor 2, with short-term skin contact (up to 30s) within intended or foreseeable use	
			a. use by children	b. other consumer products	a. use by children	b. other consumer products
Benzo(a)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(e)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(a)anthracene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(b)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(j)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(k)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Chrysene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Dibenzo(a,h)anthracene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(ghi)perylene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Indeno(1,2,3-cd)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Phenanthrene, Pyrene, Anthracene, Fluoranthene	mg/kg	<1 Sum	<5 Sum	<10 Sum	<20 Sum	<50 Sum
Naphthalene	mg/kg	<1	<2		<10	
Sum 15 PAH	mg/kg	<1	<5	<10	<20	<50

In the sum of the 15 PAH, only those PAH components quantified in the material from 0.2 mg/kg are taken into account.

TO BE CONTINUED

TEST RESULT

Total Cadmium Content

Test Request: Total cadmium content as specified in Commission Regulation (EU) 2016/217 amending entry 23 of Annex XVII of REACH Regulation (EC) No 1907/2006.

Test Method: EPA 3050B:1996, EPA 3052:1996, EN 1122:2001 Method B, acid digestion method was used and total cadmium content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result
				1
Total Cadmium	mg/kg	1000	5	ND

Remark:

As per client's request, only the appointed materials have been tested.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

END OF THE REPORT