

TEST REPORT

APPLICANT : TAISHUN ZHENXING TOYS CO., LTD

ADDRESS : JIAOYANG INDUSTRIAL PARK, TAISHUN

SAMPLE DESCRIPTION : Kids Kitchen Play Set

ITEM NO. : 350-079(TZ-D4535-B), 350-079WT(TZ-D4535-W)

AGE REQUESTED ON APPLICATION FORM : 3+

LABELED AGE GRADE : 3+

AGE GRADE APPLIED IN TESTING : Over 3 Years

LAB RECOMMENDED AGE GRADE : Over 3 Years

SAMPLE RECEIVED DATE : 01-Feb-2024

FURTHER INFORMATION DATE : 20-Feb-2024

TURN AROUND TIME : 01-Feb-2024 to 21-Feb-2024

The following test item(s) was/were performed on submitted sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Mechanical and Physical Properties	ASTM F963-23	Pass
Flammability of Toys	ASTM F963-23	Pass
Heavy Metals	ASTM F963-23	Pass
Phthalates Content	ASTM F963-23	Pass
Total Lead Content in Substrate	US CPSIA, Section 101	Pass
Total Lead Content in Paint / Surface Coating	US CPSIA, Section 101	Pass
Phthalates Content	US CPSIA, Section 108	Pass
Phthalates Content	CPSC 16 CFR part 1307	Pass

Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to info.sh@cpt.eurofinscn.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to info.sh@cpt.eurofinscn.com and referring to this report number.



***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****


Signed for and on behalf of
Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.



Gao Jian, David
Senior Manager, Toy Division



TEST SAMPLE PHOTO(S)



EFW524020097-CG-01

TO BE CONTINUED

REFERENCE SAMPLE PHOTO(S)



The reference sample(s) has not been tested in current report, but according to customer's request, the picture has also been included. For sample tested in current report, please refer to "Test sample photo".

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Sample No.
1	White paper with black/white coating	A,B
2	Multi-color coating on wood	A,B
3	Light brown/brown coating on wood	A,B
4	White coating on wood	A,B
5	Black coating on wood	A,B
6	Silver grey coating on wood	A,B
7	Blue coating on wood	A,B
8	Yellow coating on wood	A,B
9	Pink coating on wood	A,B
10	Green coating on wood	A,B
11	Dark yellow coating on wood	A,B
12	Beige yellow coating on wood	A,B
13	White coating on plastic	A,B
14	Silver grey coating on plastic	A,B
15	Dark brown coating on wood	C
16	Semi-transparent plastic (screw)	A,B,C
17	Transparent plastic (windows)	A,B
18	Semi-transparent plastic (fixed windows)	A,B
19	Brown plastic excluding coating (pot)	A,B
20	White plastic piping	A,B
21	Semi-transparent plastic	A,B
22	Grey plastic	A,B
23	Transparent red plastic	A,B
24	Transparent green plastic	A,B
25	Black plastic battery box	A,B
26	Black plastic (sink bottom)	A,B
27	Black plastic (switch)	A,B
28	Black plastic (gas stove)	A,B
29	Beige grey plastic excluding coating (gas stove)	A,B
30	Black plastic (faucet)	A,B
31	White plastic excluding coating (faucet/handle)	A,B
32	Beige plastic (handle)	A,B
33	Semi-transparent plastic (snap fastener)	A,B
34	Brown MDF excluding coating	A,B,C
35	White fabric rope	A,B
36	Natural color wood	A,B
37	Gold plated metal (screws)	A,B
38	Silver metal (long screw)	A,B
39	Silver metal magnetic rivets	A,B
40	Silver metal small (screw)	A,B
41	Silver metal (hinges)	A,B
42	Silver metal (pot/shovel)	B
43	Silver metal (handle)	B

TO BE CONTINUED

TEST RESULT

Mechanical and Physical Properties

Test Request: As specified in Consumer Safety Specification ASTM F963-23

Section	Description	Result
4.1	Material Quality	P
4.3.7	Stuffing Materials	N/A
4.5	Sound-producing Toys	P
4.6	Small Objects	N/A
4.6.1	Toys that are intended for children under 36 months of age	N/A
4.6.2	Mouth-actuated Toys	N/A
4.6.3	Toys that are intended for children over 36 months but less than 72 months	N/A
4.7	Accessible Edges	P
4.8	Projections	P
4.8.1	Bath Toy Projections	N/A
4.9	Accessible Points	P
4.10	Wires or Rods	N/A
4.11	Nails and Fasteners	P
4.12	Plastic Film	N/A
4.13	Folding Mechanisms and Hinges	N/A
4.14	Cords, Straps and Elastics	N/A
4.15	Stability and Over-load Requirements	P
4.16	Confined Spaces	N/A
4.17	Wheels, Tires, and Axles	N/A
4.18	Holes, Clearance and Accessibility of Mechanisms	N/A
4.19	Simulated Protective Devices	N/A
4.20	Pacifiers	N/A
4.21	Projectile Toys	N/A
4.22	Teethers and Teething Toys	N/A
4.23	Rattles	N/A
4.24	Squeeze Toys	N/A
4.25	Battery-operated Toys (exclude section 4.25.9 Battery-powered Ride-on Toys and section 4.25.10 Toys that Contain Secondary Cells or Secondary Batteries)	P
4.26	Toys Intended to be Attached to a Crib or Playpen	N/A
4.27	Stuffed and Beanbag-type Toys	N/A
4.28	Stroller and Carriage Toys	N/A
4.30	Toy Gun Marking	N/A
4.31	Balloons	N/A
4.32	Certain Toys with Nearly Spherical Ends	N/A
4.33	Marbles	N/A
4.34	Balls	N/A
4.35	Pompoms	N/A
4.36	Hemispheric-shaped Objects	N/A
4.37	Yo Yo Elastic Tether Toys	N/A
4.38	Magnets	N/A
4.39	Jaw Entrapment in Handles and Steering Wheels	N/A

TO BE CONTINUED

TEST RESULT

4.40	Expanding Materials	N/A
4.41	Toy Chests	N/A
5	LABELING REQUIREMENTS	
5.1	Federal Government Requirements	P
5.2	Age Grading Labeling	P
5.3	Safety Labeling Requirements	P
5.4	Aquatic Toys	N/A
5.5	Crib and Playpen Toys	N/A
5.6	Mobiles	N/A
5.7	Stroller and Carriage Toys	N/A
5.8	Toys Intended to be Assembled by an Adult	P
5.9	Simulated Protective Devices	N/A
5.10	Toys with Functional Sharp Edges or Points	N/A
5.11	Small Objects, Small Balls, Marbles and Balloons (16 CFR 1500.19)	N/A
5.12	Art Materials (16 CFR 1500.14(b)(8))	N/A
5.13	Electric Toys	N/A
5.14	Battery-operated Toys	N/A
5.14.1	Battery-powered Ride-on Toys	N/A
5.14.2	Button or Coin Cell Batteries	N/A
5.15	Promotional Materials	P
5.16	Magnets	N/A
6	INSTRUCTIONAL LITERATURE	
6.1	Definition and Description	P
6.2	Crib and Playpen Toys	N/A
6.3	Mobiles	N/A
6.4	Toys Intended to be Assembled by an Adult	P
6.5	Battery-operated Toys	P
6.6	Battery-powered Ride-on Toys	N/A
6.7	Toys in Contact with Food	N/A
6.8	Toy Chests	N/A
6.9	Manufacturer-supplied specialty or custom tools to access the battery(ies)	N/A
7	PRODUCER'S MARKINGS	
7.1	Producer's or Distributor's Name and Address	P
7.2	Battery-powered Ride-on Toys	N/A
7.3	Toy Chests	N/A

Remark:

P-Pass, F- Fail, N/A-Not Applicable, N/C-Not conduct as per client's request

TO BE CONTINUED

TEST RESULT

Flammability of Toys

Test Request: As specified in ASTM F963-23, Section 4.2, testing procedure for materials other than textiles (excluding paper) used in toys is contained in Annex A5.

Sample	Limit	Result
A	0.1 inch/second	P
B	0.1 inch/second	P

Remark:

P-Pass, F- Fail, N/A-Not Applicable

TO BE CONTINUED

TEST RESULT

Heavy Metals

1) ASTM F963-23- Heavy Elements – Total Lead in Paint and Similar Surface-Coating Material (Clause 4.3.5.1(1))
Test Method: ASTM International Standard ASTM F963-23, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				6	7	8	9	10
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				11	12	13	14	15
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

2) ASTM F963-23- Heavy Elements – Total Lead in Substrate Material (Clause 4.3.5.2(2) (a))
Test Method: ASTM International Standard ASTM F963-23, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				16	17	18	19	20
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				21	22	23	24	25
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	16	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				26	27	28	29	30
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result			
				31	32	33	34
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				36	37	38	39	40
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result		
				41	42	43
Total Lead in Substrate	mg/kg	100	10	ND	40	ND

TO BE CONTINUED

TEST RESULT

3) ASTM F963-23- Heavy Elements – Total Elements Content, Initial Screening for Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay(Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-23, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	ND	307	255	ND	203
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	12	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				6	7	8	9	10
Total Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	194	142	213	67	186
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				11	12	13	14	15
Total Antimony	mg/kg	60	5	ND	ND	ND	21	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	397	221	544	287	442
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	34
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				16	17	18	19	20
Total Antimony	mg/kg	60	5	62*	36	112*	93*	34
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	86	41	37	216	1.52x10 ^{3*}
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result				
				21	22	23	24	25
Total Antimony	mg/kg	60	5	43	70*	ND	ND	27
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	56	3.43x10 ^{3*}	22	43	1.14x10 ^{3*}
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	28	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	16	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				26	27	28	29	30
Total Antimony	mg/kg	60	5	ND	ND	26	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	71	195	75	14	ND
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				31	32	33	34	35
Total Antimony	mg/kg	60	5	15	ND	ND	ND	101*
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	636	78	ND	ND	159
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				36				
Total Antimony	mg/kg	60	5	19				
Total Arsenic	mg/kg	25	5	ND				
Total Barium	mg/kg	1000	10	ND				
Total Cadmium	mg/kg	75	5	ND				
Total Chromium	mg/kg	60	5	ND				
Total Lead	mg/kg	90	10	ND				
Total Mercury	mg/kg	60	5	ND				
Total Selenium	mg/kg	500	10	ND				

TO BE CONTINUED

TEST RESULT

4) ASTM F963-23- Heavy Elements – Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay (Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-23, Section 8.3.2 to 8.3.5 (excluding 8.3.5.5(3))

Tested Item(s)	Unit	Limit	MDL	Result				
				16	18	19	20	22
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result	
				25	35
Soluble Antimony	mg/kg	60	5	ND	ND
Soluble Arsenic	mg/kg	25	5	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND
Soluble Lead	mg/kg	90	10	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

The analytical results were adjusted by subtracting analytical correction factor.

* On the initial analysis for soluble heavy metals content, any tested component of greater than the set limit, the result is inconclusive for the requirement and therefore were retested with soluble heavy metals analysis of ASTM F963-23, Sections 8.3.2 to 8.3.5 as specified in Section 8.3.1.3. The result herein is for reference only (show data), please refer to soluble heavy metals content analysis for the corresponding conclusive results.

According to Section 8.3.1.3, if results of total eight elements are below soluble limits for each element as prescribed in the table, the material can be considered to conform to requirements of 4.3.5.1(2) or 4.3.5.2(2)(b), or both, without further testing.

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content in Toys (including pacifiers, rattles, and teethers) Material (ASTM F963-23, Section 4.3.8)

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1	2	3	4+5+6
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					7+8+9	10+11+12	13+14+15	16+17+18
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					19+20+21	22+23+24	25+26+27	28+29+30
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					31+32+33
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND

Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Total Lead Content in Substrate

Test Request: Total lead in substrate as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1001-08.3 for metal product, CPSC-CH-E1002-08.3 for nonmetal product.
The sample was acid digested, and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result				
				16	17	18	19	20
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				21	22	23	24	25
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	16	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				26	27	28	29	30
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result			
				31	32	33	34
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				36	37	38	39	40
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result		
				41	42	43
Total Lead in Substrate	mg/kg	100	10	ND	40	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Total Lead Content in Paint / Surface Coating

Test Request: Total lead in paint/ similar surface coatings as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1003-09.1
The sample was acid digested, and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				6	7	8	9	10
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				11	12	13	14	15
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 108

Test Method: CPSC-CH-C1001-09.3

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1	2	3	4+5+6
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.0050	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.0050	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.0050	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.0050	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.0050	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.0050	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					7+8+9	10+11+12	13+14+15
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.0050	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.0050	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.0050	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.0050	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.0050	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.0050	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					16+17+18	19+20+21	22+23+24
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.0050	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.0050	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.0050	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.0050	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.0050	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.0050	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					25+26+27	28+29+30	31+32+33
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.0050	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.0050	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.0050	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.0050	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.0050	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.0050	ND	ND	ND

Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates as specified in CPSC 16 CFR part 1307.

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1	2	3	4+5+6
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					7+8+9	10+11+12	13+14+15
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					16+17+18	19+20+21	22+23+24
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					25+26+27	28+29+30	31+32+33
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

END OF THE REPORT