



CONSUMER PRODUCTS SERVICES DIVISION

Technical Report: (6619)185-0532
Date Received: JUL.04, 2019
Mod. Date: /

JUL.11, 2019
Page 1 of 4

ZHAO YONG
ANJI JINTAI LEATHER TRADING CO.,LTD
ZHEJIANG HUZHOU ANJI COUNTY SWIVEL CHAIR
MARKET 4301

Sample Description:	PU	PO No.:	/
Manufacturer:	/	Style No	JRU-052
Buyer:	/	Country of Destination:	/
Country of Origin:	/	SKU No.:	/
Color:	RED	Previous Report No.:	/
Protocol No.:	/		

EXECUTIVE SUMMARY:

TEST REQUESTED		CONCLUSION	Remark
1)	Technical Bulletin 117 -2013 Section I(Cover Fabric)	PASS	See test result on page 3

REMARK:

The client specifies the test methods and requirements.



ANJI JINTAI LEATHER TRADING CO.,LTD
Technical Report: **(6619)185-0532**
JUL.11, 2019
Page 2 of 4

BVCPS (SHANGHAI) GENERAL CONTACT INFORMATION FOR THIS REPORT

TELEPHONE NO 86-21-24166888
E-MAIL: bvcpshtoy.sh@cn.bureauveritas.com

BUREAU VERITAS
CONSUMER PRODUCTS SERVICE DIVISION (SHANGHAI)
Laboratory Test location:
No. 368, Guangzhong Road, Zhuanqiao Town, Minhang,
Shanghai.
No. 168, Guanghua Road, Zhuanqiao Town, Minhang, Shanghai.

Hyde Bao
PRODUCT LINE MANAGER(HARDLINE DIVISON)



1. Technical Bulletin 117 -2013 Section I(Cover Fabric)


Specimen No.	Smoldering time (>45min or Not)	Char Length / in	Requirement	Rating
1	Not	0	Maximum char length of any specimen shall not exceed 1.8 inches	PASS
2	Not	0		PASS
3	Not	0		PASS

Tested Item(s): Red PU

Remark:

1. If the specimen continues to smolder after the 45 minute test duration, the barrier material fails the test.
2. If more than one initial specimen fails, the barrier material fails the test.
3. If any one of the three initial specimens fails, repeat the test on additional three specimens. Record the additional test specimens result in new datasheet and provide the Final Overall Rating.
4. If all three additional specimens pass the test, the barrier material passes the test. If any one of the additional three specimens fails, the barrier material sample fails the test.

EXHIBIT



END