


REPORT

Technical Report: (8522)152-0019

Page 1 of 4
June 7, 2022





Sample Description:	FOAM														
Manufacturer:	/										P.O. No.:	/			
Buyer:	/										Style:	/			
Country of Origin:	/										Country of Destination:	/			
Color:	/										SKU Number:	/			
Re-test:	Yes:			No:	X					Charge Vendor:	Yes:	X	No:		
Previous Report No.:	/														



EXECUTIVE SUMMARY:

1. The submitted resilient filling material sample(s) demonstrated **SATISFACTORY** flammability characteristics in testing of California Technical Bulletin 117 Section 3 as the following result conform to the test requirement.(**PASS**)

Flammability of Resilient filling materials test

Test Method : California Technical Bulletin CA TB 117-2013 section III

RESULT FOR INITIAL TEST			
SPECIMEN	TRANSITION TO OPEN FLAMING	SMOLDERING	CHAR LENGTH(IN)
1	No	No	0.8
2	No	No	0.6
3	No	No	0.6
OVERALL RATING		PASS	

REMARK(S):

1. No protocol was enclosed for test results.
2. Per request, only California Technical Bulletin 117-2013 section III was conducted in this report.

NOTE: If there are questions or concerns regarding above report, please contact the appropriate lab persons.

Technical questions & concerns:

Peter Wan / Laura Liu
(+86)755-32980233 / 32980236
Peter.wan@bureauveritas.com
Laura.liu@bureauveritas.com

General Enquiries:

Tina He / Grace Gao
(+86)755-32980210 / 86135512
Tina.he@bureauveritas.com
Grace.gao@bureauveritas.com

BUREAU VERITAS SHENZHEN CO., LTD



BRIAN TAM
MANAGER – HARDLINES DIVISION

END OF REPORT