



Original Picture









Applicant : Tianjin U-Living Home Decor Co., Ltd

Date : Apr 08, 2025

Attn : Wheeler

Sample Description As Declared :

No. Of Sample : Seven
Fibre Content : 100% Polyester
Material : Rug, size: (A/B)160X230CM (C/D/E/F/G) 5'X7'
Finishing : Without Flame Retardant
End Uses : Adult's Rug
Colour : (A) 36610YC-1 (B) 36610YC (C) 37761ZC (D) 37764ZC-1 (E) 41550YA
(F) 38073ZA-1 (G) 41551YA
Style No. : 83C-040V70BK,83C-040V71BK,83C-040V72BK,83C-040V70BN,83C-040V71BN,
83C-040V72BN,83C-048V00YL,83C-048V01YL,83C-048V02YL,83C-049V00BU,
83C-049V01BU,83C-049V02BU,83C-050V00BU,83C-050V01BU,83C-050V02BU,
83C-051V00LR,83C-051V01LR,83C-051V02LR,83C-052V00MX,83C-052V01MX,
83C-052V02MX
Order No./PO No. : 25A7714 25A7657
Buyer's Name : Aosom
Agent's Name : -
Manufacturer's Name : Tianjin U-Living Home Decor Co., Ltd


Applicant's Provided Care Instruction/Label : -

Date Received/Date Test Started : Apr 01, 2025

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(S)

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.



Patrick Gong
General Manager

Conclusion:


<u>Tested Component/Sample</u>	<u>Test Item</u>	<u>Result</u>
(B1)	Azocolourants Content Requirement in Annex XVII Item 43 and 72 of the REACH Regulation (EC) No. 1907/2006 & Its Amendments	Pass
(C&E)	California Proposition 65 Assessment	Pass
(C1/E1)	Phthalate Content Requirement Of The Consent Judgment No. CIV-05991 Settled By Superior Court Of The State Of California For The County Of Marin, For Vinyl Floor Mats, Floor Tiles And Floor Coverings Based On The California Proposition 65.	Pass

	(A)	(D)	(F)	(G)
Flammability Test	N/A	-	-	-
Flammability Test For Carpets And Rugs	-	M	M	M

Remark: M=Based Upon The Results Of The Flammability Test Reported, The Sample Submitted For Testing Meets The Performance Requirements Of 16 CFR Part 1630 (FF1-70).

N/A = Not Applicable

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.



Patrick Gong
General Manager

Tests Conducted:

1 Flammability Test (BS 6307-1982/ISO 6925-1982):

The Apparatus And Methods Of Testing Were Those Described In BS 6307/ISO 6925.

The Following Test Results Relate Only To Assess The Properties Of Materials Or Systems In Response To Heat And Flame Under Controlled Laboratory Conditions And Should Not Be Used For The Evaluation Or Regulation Of The Hazard Of Textile Floor Coverings Under Actual Fire Conditions

Sample Reference:

Pre Conditioning : Minimum 24 Hours 20±2°C And 65±2% Relative Humidity

Test Atmosphere : 10°C - 30°C, 20% - 65% Relative Humidity

Test Result:

Sample (A)

Sample No.	Maximum Length From Centre To The Edge Of Damage (mm)	Flame Spread Time (Seconds)
1	10	N/A
2	09	N/A
3	08	N/A
4	10	N/A
5	11	N/A
6	09	N/A
7	09	N/A
8	10	N/A

Remark : N/A = Not Applicable

The Test Was Conducted By Intertek Testing Services Shanghai Ltd.

Tests Conducted :

2 Flammability Test For Carpets And Rugs (US CPSC 16 CFR Part 1630) :

The Apparatus And Methods Of Testing Were Those Described In 16 CFR Part 1630 Standard For The Surface Flammability Of Carpets And Rugs (FF1-70).

Requirement

(1) Test Criterion:

The Charred Portion Does Not Extend To Within One Inch Of The Edge Of The Hole In The Flattening Frame At Any Point.

(2) Acceptance Criterion:

At Least 7 Of The 8 Specimens Must Meet The Test Criterion For The Material To Be Classified As Resistance To Flammability.

Sample (D)

Test Result :

The Nearest Distance From Burnt Area To The Frame Edge

	<u>Original</u> (Inch)
3.2	3.2
3.1	3.3
3.2	3.2
3.2	3.2

Interpretation Of Test Result :

Number Of Specimens Meet The Test Criterion	8
---	---

Sample (F)

Test Result :

The Nearest Distance From Burnt Area To The Frame Edge

	<u>Original</u> (Inch)
3.2	3.3
3.3	3.2
3.2	3.1
3.2	3.2

Interpretation Of Test Result :

Number Of Specimens Meet The Test Criterion	8
---	---

Tests Conducted :

Flammability Test For Carpets And Rugs(Cont'd)

Sample (G)

Test Result :

The Nearest Distance From Burnt Area To The Frame Edge

	<u>Original</u> (Inch)	
3.2		3.2
3.1		3.3
3.3		3.1
3.2		3.1

Interpretation Of Test Result :

Number Of Specimens

Meet The Test Criterion

8

Tests Conducted :

3 Detection of Amines Derived from Azocolourants and Azodyes:

By Gas Chromatographic - Mass Spectrometric (GC-MS) Analysis.

Test Method: EN ISO 14362-1: 2017 for Textile Material

No.	Forbidden Amine	Cas No.	Result (mg/kg) Method D (B1)
1.	4-Aminodiphenyl	92-67-1	ND
2.	Benzidine	92-87-5	ND
3.	4-Chloro-o-Toluidine	95-69-2	ND
4.	2-Naphthylamine	91-59-8	ND
5.	o-Aminoazotoluene	97-56-3	ND
6.	2-Amino-4-Nitrotoluene	99-55-8	ND
7.	p-Chloroaniline	106-47-8	ND
8.	2,4-Diaminoanisole	615-05-4	ND
9.	4,4'-Diaminodiphenylmethane	101-77-9	ND
10.	3,3'-Dichlorobenzidine	91-94-1	ND
11.	3,3'-Dimethoxybenzidine	119-90-4	ND
12.	3,3'-Dimethylbenzidine	119-93-7	ND
13.	3,3'-Dimethyl-4,4'diaminodiphenylmethane	838-88-0	ND
14.	p-Cresidine	120-71-8	ND
15.	4,4'-Methylene-Bis(2-Chloroaniline)	101-14-4	ND
16.	4,4'-Oxydianiline	101-80-4	ND
17.	4,4'-Thiodianiline	139-65-1	ND
18.	o-Toluidine	95-53-4	ND
19.	2,4-Toluylenediamine	95-80-7	ND
20.	2,4,5-Trimethylaniline	137-17-7	ND
21.	2-Methoxyaniline	90-04-0	ND
22.	4-aminoazobenzene	60-09-3	ND
23.	4-chloro-o-toluidinium chloride (detection by 4-Chloro-o-toluidine)	3165-93-3	ND
24.	2-Naphthylammoniumacetate (detection by 2-Naphthylamine)	553-00-4	ND
25.	4-methoxy-m-phenylene diammonium sulphate (detection by 4-methyl-m-phenylenediamine)	39156-41-7	ND
26.	2,4,5-trimethylaniline hydrochloride (detection by 2,4,5-trimethylaniline)	21436-97-5	ND

Tests Conducted :

Detection of Amines Derived from Azocolourants and Azodyes(Cont'd)

Remark: ND = Not Detected
Detection Limit = 5 mg/kg
Requirement: 30 mg/kg

Method D: Colourant extraction with Xylene as per EN ISO 14362-1: 2017 Section 10.1

Tested Components:
(B1)Multicolor 100% Polyester Main Fabric For Sample(B)Use

4 California Proposition 65 Assessment :

Sample (C&E)

The Submitted Sample(s) Was Reviewed Against Intertek California Proposition 65 Protocol (Issue No. 47 Dated Dec 18, 2024). According To Consent Judgment No. CIV-05991 Of Court Case, Testing Item Phthalates Content Need To Be Conducted.

Requirement

Meet The
Requirement CA
Prop 65

5 Phthalate Content Test :

By Solvent Extraction And Gas Chromatographic-Mass Spectrometric (GC-MS) Analysis.

	<u>Result (% , w/w)</u> (C1/E1)	<u>Limit (% , w/w)(max.)</u>
Diethyl hexyl phthalate (DEHP)	ND	0.1
Benzyl butyl phthalate (BBP)	ND	0.1

Remark : The Above Limit Was Quoted From The Consent Judgment No. CIV-05991 Settled By Superior Court Of The State Of California For The County Of Marin, For Vinyl Floor Mats, Floor Tiles And Floor Coverings Based On The California Proposition 65.

ND = Not Detected
Detection Limit = 0.01%(w/w)

Tested Components:
(C1) Transparent PVC Coating On Rug Back For Sample (C) Used
(E1) Transparent PVC Coating On Rug Back For Sample (E) Used

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.