

TEST REPORT

<u>Applicant</u>	: PINGHU XH CHILDREN PRODUCTS CO., LTD
<u>Address</u>	: NO.186, TONGCHE ROAD, XINCANG TOWN, PINGHU CITY, ZHEJIANG PROVINCE
<u>Sample description</u>	: Electric Ride-on Car
<u>Item no.</u>	: Shelby GT 350/JC311/JC312
<u>Manufacturer</u>	: PINGHU XH CHILDREN PRODUCTS CO., LTD
<u>Lab recommended age grade</u>	: Over 3 Years
<u>Age requested on application form</u>	: 3+
<u>Labelled age grade</u>	: Age 3+
<u>Age grade applied in testing</u>	: Over 3 Years
<u>Sample received date</u>	: 08-Jan-2025
<u>Further information date</u>	: 24-Mar-2025
<u>Turn around time</u>	: 08-Jan-2025 To 26-Mar-2025

The following test item(s) was/were performed on submitted sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Physical and Mechanical Hazards	ASTM F963-23	Pass
Flammability of Toys	ASTM F963-23, Section 4.2	Pass
Phthalates Content	ASTM F963-23, Section 4.3.8	Pass
Heavy Metals	ASTM F963-23, Section 4.3.5	Pass
Total Lead Content in Substrate	US CPSIA, Section 101 (15 U.S.C. § 1278a)	Pass
Phthalates Content	US CPSIA, Section 108	Pass
Total Lead Content in Paint / Surface Coating	US CPSIA, Section 101 (15 U.S.C. § 1278a)	Pass
Phthalates Content	CPSC 16 CFR part 1307	Pass
Total Lead Content in Paint and Similar Surface-coating Materials	US 16 CFR 1303	Pass
Physical and Mechanical Hazards	CPSC Regulations	Pass
Tracking Label Assessment	US CPSIA, Section 103	Pass

Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to info.sh@cpt.eurofinscn.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to info.sh@cpt.eurofinscn.com and referring to this report number.




***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.




Gao Jian, David
Toy Division Senior Manager SL TH

TEST SAMPLE PHOTO(S)



EFW525010285-CG-02

TO BE CONTINUED

REFERENCE SAMPLE PHOTO(S)



The reference sample(s) has not been tested in current report, but according to customer's request, the picture has also been included. For sample tested in current report, please refer to "Test sample photo".

TO BE CONTINUED

REFERENCE SAMPLE PHOTO(S)



The reference sample(s) has not been tested in current report, but according to customer's request, the picture has also been included. For sample tested in current report, please refer to "Test sample photo".

TO BE CONTINUED

REFERENCE SAMPLE PHOTO(S)



The reference sample(s) has not been tested in current report, but according to customer's request, the picture has also been included. For sample tested in current report, please refer to "Test sample photo".

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Sample No.
1	Orange coating on plastic	B
2	White coating on plastic film sticker	B
3	Black coating on plastic	A
4	White coating on plastic (button keys)	A,B
5	Silver coating on plastic	A,B
6	Black coating on metal	A,B
7	Multi-color coating on plastic	A,B
8	Black plastic (wheel)	A,B
9	Transparent plastic (seat)	A,B
10	Black plastic (seat belt buckle)	A,B
11	Blue plastic (body)	A
12	Transparent black plastic	A,B
13	Black plastic (steering wheel)	A,B
14	Red plastic (buttons on steering wheel)	A,B
15	Silver gray plastic (hub cover)	A,B
16	Transparent plastic (door)	A,B
17	Silver grey plastic (on door)	A,B
18	Black plastic (on remote control)	A
19	White plastic (remote control)	A
20	Transparent black plastic (indicator light on remote control)	A
21	Black plastic (brake)	A,B
22	White plastic (display panel)	A,B
23	Bright black plastic excluding coating (button keys)	A,B
24	White plastic (interface)	A,B
25	Black plastic (interface)	A,B
26	Transparent plastic (radio display screen)	A,B
27	Transparent plastic (car lights)	A,B
28	Black plastic (base)	A,B
29	Black plastic (front)	A,B
30	Transparent red plastic (car rear light)	A,B
31	Silver grey plastic (behind)	A,B
32	Black plastic (base on bottom)	A,B
33	Black plastic (motor)	A,B
34	White plastic (on motor)	A,B
35	Light blue plastic (body)	B
36	Black plastic	C
37	White plastic	C
38	Orange plastic	C
39	Red plastic	C
40	Pink plastic	C
41	Rose purple plastic	C
42	Grass green plastic	C
43	Grey green plastic	C
44	White soft plastic film sticker excluding coating	A,B
45	Black plastic with bright silver plating (handle)	A,B
46	White paper sticker with transparent plastic film and underlying black/white coating	A
47	Black fabric (seat belt)	A,B

TO BE CONTINUED

Component No.	Component	Sample No.
48	Black plated metal (screws)	A,B
49	Silver metal (interface)	A,B
50	Silver metal (screws/on remote control	A
51	Silver metal (large screws/washers)	A,B
52	Silver metal excluding coating (rod/base)	A,B

TO BE CONTINUED

TEST RESULT

Physical and Mechanical Hazards

Test Request: As specified in Consumer Safety Specification ASTM F963-23

Test Sample: A,B

Section	Description	Result
4.1	Material Quality	P
4.3.7	Stuffing Materials	N/A
4.5	Sound-Producing Toys	P
4.6	Small Objects	N/A
4.6.1	Toys that are intended for children under 36 months of age	N/A
4.6.2	Mouth-Actuated Toys	N/A
4.6.3	Toys that are intended for children over 36 months but less than 72 months	N/A
4.7	Accessible Edges	P
4.8	Projections	P
4.8.1	Bath Toy Projections	N/A
4.9	Accessible Points	P
4.10	Wires or Rods	N/A
4.11	Nails and Fasteners	P
4.12	Plastic Film	P
4.13	Folding Mechanisms and Hinges	N/A
4.14	Cords, Straps and Elastics	N/A
4.15	Stability and Over-Load Requirements	P
4.16	Confined Spaces	N/A
4.17	Wheels, Tires, and Axles	P
4.18	Holes, Clearances, and Accessibility of Mechanisms	N/A
4.19	Simulated Protective Devices	N/A
4.20	Pacifiers	N/A
4.21	Projectile Toys	N/A
4.22	Teethers and Teething Toys	N/A
4.23	Rattles	N/A
4.24	Squeeze Toys	N/A
4.25	Battery-Operated Toys (exclude section 4.25.9 Battery-powered ride-on toys and section 4.25.10 Toys contain secondary cells or secondary batteries)	P
4.26	Toys Intended to be Attached to a Crib or Playpen	N/A
4.27	Stuffed and Beanbag-Type Toys	N/A
4.28	Stroller and Carriage Toys	N/A
4.30	Toy Gun Marking	N/A
4.31	Balloons	N/A
4.32	Certain Toys with Nearly Spherical Ends	N/A
4.33	Marbles	N/A
4.34	Balls	N/A
4.35	Pompoms	N/A
4.36	Hemispheric-Shaped Objects	N/A
4.37	Yo Yo Elastic Tether Toys	N/A
4.38	Magnets	N/A
4.39	Jaw Entrapment in Handles and Steering Wheels	N/A
4.40	Expanding Materials	N/A

TO BE CONTINUED

TEST RESULT

Section	Description	Result
4.41	Toy Chests	N/A
5	Labeling Requirements	
5.1	Federal Government Requirements	P
5.2	Age Grading Labeling	P
5.3	Safety Labeling Requirements	P
5.4	Aquatic Toys	N/A
5.5	Crib and Playpen Toys	N/A
5.6	Mobiles	N/A
5.7	Stroller and Carriage Toys	N/A
5.8	Toys Intended to be Assembled by an Adult	P
5.9	Simulated Protective Devices	N/A
5.10	Toys with Functional Sharp Edges or Points	N/A
5.11	Small Objects, Small Balls, Marbles and Balloons	N/A
5.12	Art Materials	P
5.13	Electric Toys	N/A
5.14	Battery-Operated Toys	N/A
5.14.1	Battery-Powered Ride-On Toys	N/A
5.14.2	Button or Coin Cell Batteries	N/A
5.15	Promotional Materials	P
5.16	Magnets	N/A
6	Instructional Literature	
6.1	Definition and Description	P
6.2	Crib and Playpen Toys	N/A
6.3	Mobiles	N/A
6.4	Toys Intended to be Assembled by an Adult	P
6.5	Battery-Operated Toys	P
6.6	Battery Powered Ride-On Toys	P
6.7	Toys in Contact with Food	N/A
6.8	Toy Chests	N/A
6.9	The instructional material for toys which require a manufacturer-supplied specialty or custom tool to access the battery (ies)	N/A
7	Producer's Markings	
7.1	Producer's or Distributor's Name and Address	P
7.2	Battery-Powered Ride-on Toys	N/A
7.3	Toy Chests	N/A

Remark:

P-Pass, F- Fail, N/A-Not Applicable, N/C-Not conduct as per client's request

TO BE CONTINUED

TEST RESULT

Flammability of Toys

Test Request: As specified in ASTM F963-23, Section 4.2, testing procedure for materials other than textiles (excluding paper) used in toys is contained in Annex A5.

Sample	Limit	Result
A	0.1 inch/second	P
B	0.1 inch/second	P

Remark:

P-Pass, F- Fail, N/A-Not Applicable

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content in Toys (including pacifiers, rattles, and teethers) Material (ASTM F963-23, Section 4.3.8)

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+3	4+5+6	7	8+9+10
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					11+12+13	14+15+16	17+18+19	20+21+22
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					23+2 4+25	26+2 7+28	29+3 0+31	32+3 3+34
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					35+3 6+37	38+3 9+40	41+4 2+43	44
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					45	46
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND

Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Heavy Metals

1) ASTM F963-23- Heavy Elements – Total Lead in Paint and Similar Surface-Coating Material (Clause 4.3.5.1(1))
Test Method: ASTM International Standard ASTM F963-23, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result	
				6	7
Total Lead in Paint	mg/kg	90	10	ND	ND

2) ASTM F963-23- Heavy Elements – Total Lead in Substrate Material (Clause 4.3.5.2(2) (a))
Test Method: ASTM International Standard ASTM F963-23, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				8	9	10	11	12
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				13	14	15	16	17
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				18	19	20	21	22
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				23	24	25	26	27
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				28	29	30	31	32
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				33	34	35	36	37
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				38	39	40	41	42
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				43	44	45	46	48
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result			
				49	50	51	52
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

3) ASTM F963-23- Heavy Elements – Soluble Migrated Elements Content in Surface Coatings and Substrates
Other Than Modeling Clay (Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-23, Section 8.3.2 to 8.3.5 (excluding 8.3.5.5(3))

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	5	7
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				8	9	10	11	12
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				13	14	15	16	17
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				18	19	20	21	22
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result				
				23	24	25	26	27
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				28	29	30	31	32
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				33	34	35	36	37
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				38	39	40	41	42
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result				
				43	44	45	46	47
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Remark:

The test result of component No.4,6 of migrated elements content is not applicable due to the sample weight of test portion is less than 10 mg.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

The analytical results were adjusted by subtracting analytical correction factor.

The test result of component No.7,20,46 of soluble migrated elements content was calculated as if 100 mg of test portion had been used and the sample weight of test portion is less than 100 mg.

TO BE CONTINUED

TEST RESULT

Total Lead Content in Substrate

Test Request: Total lead in substrate as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101 (15 U.S.C. § 1278a).

Test Method: CPSC-CH-E1001-08.3 for metal product, CPSC-CH-E1002-08.3 for nonmetal product. The sample was acid digested, and total lead content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				8+9+10	11+12+13	14+15+16	17+18+19
Total Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				20+21+22	23+24+25	26+27+28	29+30+31
Total Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				32+33+34	35+36+37	38+39+40	41+42+43
Total Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				44	45	46	48
Total Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result	
				49+50+51	52
Total Lead (Pb)	mg/kg	100	10	ND	ND

Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 108
Test Method: CPSC-CH-C1001-09.3

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+3	4+5+6	7	8+9+10
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					11+12+13	14+15+16	17+18+19	20+21+22
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					23+24+25	26+27+28	29+30+31	32+33+34
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					35+3 6+37	38+3 9+40	41+4 2+43	44
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					45	46
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND

Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Total Lead Content in Paint / Surface Coating

Test Request: Total lead in paint/ similar surface coatings as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101 (15 U.S.C. § 1278a).

Test Method: CPSC-CH-E1003-09.1
The sample was acid digested, and total lead content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result		
				1+2+3	4+5+6	7
Total Lead (Pb)	mg/kg	90	10	ND	ND	ND

Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates as specified in CPSC 16 CFR part 1307.

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+3	4+5+6	7	8+9+10
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					11+12+13	14+15+16	17+18+19	20+21+22
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					23+2 4+25	26+2 7+28	29+3 0+31	32+3 3+34
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					35+3 6+37	38+3 9+40	41+4 2+43	44
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					45	46
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND

Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Total Lead Content in Paint and Similar Surface-coating Materials

Test Request: Total lead content as specified in US 16 CFR 1303

Test Method: CPSC-CH-E1003-09.1

The sample was acid digested, and total lead content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result		
				1+2+3	4+5+6	7
Total Lead (Pb)	mg/kg	90	10	ND	ND	ND

Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Physical and Mechanical Hazards

Test Request: The Mechanical Hazards Requirements of 16 CFR 1500, after Use and Abuse Tests.
Test Sample: A,B

Section	Description	Result
16 CFR 1501	Small Parts	N/A
16 CFR 1500.48	Sharp Points	N/A
16 CFR 1500.49	Sharp Edges	P
16 CFR 1510	Rattles	N/A
16 CFR 1511	Pacifier	N/A

Remark:

P - Pass, N/A - Not Applicable

The use and abuse tests conducted are:

As Received & Normal Use (1500.50)

Impact Test (1500. 53(b))

Torque Test (1500. 53(e))

Tension Test (1500. 53(f))

TO BE CONTINUED

TEST RESULT

Tracking Label Assessment

Test Request: As per Consumer Product Safety Improvement Act (CPSIA) 2008 section 103 tracking labels for children products

Test Sample: A,B

Labeling Content	Observation Result	Location	Conclusion
Name of Manufacturer/ Import / Private Labeler in the tracking label	Present	Packaging Product	Pass
Location of production	Present	Packaging Product	Pass
Date of production	Present	Packaging Product	Pass
Cohort information (including the batch, run number, or other identifying characteristic)	Present	Packaging Product	Pass

Remark:

The tracking label assessment was based on the submitted sample and the information provided by the applicant. There was no verification on the validity of such information.

END OF THE REPORT