



Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28

Applicant: Fujian Zhangping D-road Forestry Co.,Ltd
Address: Fushan Industry District,Zhangping City,Fujian,China,364400
Sample Description: Kid's playhouse 2284
Country of Origin: China
Receipt Date of Sample: 2024-02-26, 2024-09-18
Date of Testing: 2024-03-05 ~ 2024-04-10
2024-10-08 ~ 2024-10-28
Sample Submitted: The sample(s) was (were) submitted by applicant and identified.
Test Result: Refer to the data listed in following pages

Test Item	Conclusion
1. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety - Physical and Mechanical	Pass
2. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety - Flammability Test of Materials Other Than Textile Materials	Pass
3. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety - Flammability Test of Textile Materials	Not Applicable
4. ASTM F963-23 Section 4.3.5.1 - Total Lead Content Test (Paint and Similar Surface-Coating Materials)	Pass
5. ASTM F963-23 Section 4.3.5.2 - Total Lead Content Test (Substrate Materials)	Pass
6. ASTM F963-23 Section 4.3.5.1 & Section 4.3.5.2 - Soluble Heavy Elements	Pass
7. ASTM F963-23 Section 4.3.8 - Phthalates	Pass
8. 16 CFR Part 1303 - Total Lead Content	Pass
9. CPSIA section 101(f) -Total Lead Content (surface coating)	Pass
10. CPSIA section 101(a)(2) - Total Lead Content (Substrate)	Pass
11. CPSIA, § 108, 16 CFR 1307- Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates	Pass

Remarks: 1. MDL = Method Detection Limit
2. ND = Not Detected (<MDL)
3. ≤ Less than
4. 1 mg/kg = 1 ppm = 0.0001%
5. The test items and samples were specified by the client.
6. This report is based on report 68.452.24.0258.02 issued on 2024-04-10. Supplemental test component was tested.

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuv sud.com
Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Testing Center

Prepared by:

Authorized by:

Gianna



Steven

Kionna

Gianna Gao
Project Manager

Steven Shu
Senior Project
Coordinator
(For Chemical)

Kionna Lin
Project Manager
(For Physical and Mechanical)

Note:

- (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.
Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.
For further details, please see "Testing and certification regulation", chapter A-3.4
For full version, please visit: EN : <https://www.tuvsud.cn/zh-cn/resource/terms-and-conditions---en> ; SCN: <https://www.tuvsud.cn/zh-cn/terms-and-conditions> ; TCN: <https://www.tuvsud.com/zh-tw/terms-and-conditions>
- (2) The results relate only to the Items tested.
- (3) The test report shall not be reproduced except in full without the written approval of the laboratory
- (4) If relevant standards do not specify decision rule(s), follow decision rule as below:
 - "Pass" means that the measured result is within the limits, even when extended by expanded uncertainty at a level of confidence of 95%.
 - "Fail" means that the measured result is beyond the limit, even when extended by expanded uncertainty at a level of confidence of 95%.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuvsud.com
Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing
Lab 2 - Physical & mechanical
testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China
Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



Description of Tested Subject:

Sample	Description	Photo
A	Whole product	  

T. No	Sample	Description
T1	001	Whole product (Kid's playhouse 2284)
T2	002	White plastic (Window)
T3	003	Grey coating (Board)
T4	004	Orange coating (Board)
T5	005	White coating (Board)
T6	008	Iridescent metal (Hinge)
T7	020	Blue coating (Board)
T8	021	Bright yellow coating (Board)

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



Test Result(s):

1. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety - Physical and Mechanical

Sample	001
Labelled age range	3-7 years
Requested age range	From 3 to 7 years
Age range in testing	Over 2 years
Age Group Assessed As per Age Guideline	Over 2 years

Clause	Requirement	Evaluation
4	Safety Requirements	--
4.1	Material Quality	P
4.6	Small Objects	P
4.7	Accessible Edges	P
4.9	Accessible Points	P
4.11	Nails and Fasteners	P
4.12	Plastic Film	P
4.13	Folding Mechanisms and Hinges	P
4.15	Stability and Over-load Requirements	P
4.16	Confined Spaces	P
4.38	Magnets	P
5	Labeling Requirements	--
5.1.2	Tracking Label	P
5.2	Age Grading Labeling	P
5.3	Safety Labeling Requirements	P
5.8	Toys Intended to be Assembled By an Adult	P
5.15	Promotional Materials	P
6	Instructional Literature	--
6.1	Definition and Description	P
6.4	Toys Intended to be Assembled By an Adult	P
7	Producer's Markings	--
7.1	Name and Address of the Producer or Distributor	P

Abbreviation:

P = Pass, F = Fail, NA = Not Applicable, NR = Not Requested.

Note:

Only applicable sections were shown.

2. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety - Flammability Test of Materials Other Than Textile Materials

As per Section 4.2 of ASTM F963-23 Standard Consumer Safety Specification for Toy Safety

Sample: 001

Result: Did Not Ignite

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



3. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety - Flammability Test of Textile Materials

As per Section 4.2 of ASTM F963-23 Standard Consumer Safety Specification for Toy Safety

Sample: 001

Result: Not Applicable

4. ASTM F963-23 Section 4.3.5.1 - Total Lead Content Test (Paint and Similar Surface-Coating Materials)

Test with reference to CPSC-CH-E1003-09.1, determination by ICP-OES

Sample	Unit	MDL	Limit	Result(s)	Conclusion
003+004+005	mg/kg	10.0	90	ND	Pass
020	mg/kg	10.0	90	ND	Pass
021	mg/kg	10.0	90	ND	Pass

5. ASTM F963-23 Section 4.3.5.2 - Total Lead Content Test (Substrate Materials)

Test with reference to CPSC-CH-E1001-08.3 or CPSC-CH-E1002-08.3, determination by ICP-OES

Sample	Unit	MDL	Limit	Result(s)	Conclusion
002	mg/kg	10.0	100	ND	Pass
008	mg/kg	10.0	100	ND	Pass

6. ASTM F963-23 Section 4.3.5.1 & Section 4.3.5.2 - Soluble Heavy Elements

Test with reference to ASTM F963-23 Section 8.3, analysis was performed by ICP-MS.

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			002	003
Soluble Antimony (Sb)	5.0	60	ND	ND
Soluble Arsenic (As)	2.5	25	ND	ND
Soluble Barium (Ba)	5.0	1000	ND	7.42
Soluble Cadmium (Cd)	5.0	75	ND	ND
Soluble Chromium (Cr)	5.0	60	ND	ND
Soluble Lead (Pb)	5.0	90	ND	ND
Soluble Mercury (Hg)	5.0	60	ND	ND
Soluble Selenium (Se)	5.0	500	ND	ND
Conclusion			Pass	Pass

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			004	005
Soluble Antimony (Sb)	5.0	60	ND	ND
Soluble Arsenic (As)	2.5	25	ND	ND
Soluble Barium (Ba)	5.0	1000	5.10	49.7
Soluble Cadmium (Cd)	5.0	75	ND	ND
Soluble Chromium (Cr)	5.0	60	ND	ND
Soluble Lead (Pb)	5.0	90	ND	ND
Soluble Mercury (Hg)	5.0	60	ND	ND
Soluble Selenium (Se)	5.0	500	ND	ND
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			020	021
Soluble Antimony	5.0	60	ND	ND
Soluble Arsenic	5.0	25	ND	ND
Soluble Barium	5.0	1000	ND	ND
Soluble Cadmium	5.0	75	ND	ND
Soluble Chromium	5.0	60	ND	ND
Soluble Lead	5.0	90	ND	ND
Soluble Mercury	5.0	60	ND	ND
Soluble Selenium	5.0	500	ND	ND
Conclusion			Pass	Pass

- Remark:
- Adjusted analytical result.
 - The test results of the sample 002 is transferred from sample 011 of report 68.452.23.2025.
 - The test results of the sample 003 is transferred from sample 002 of report 68.452.23.2309.

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



7. ASTM F963-23 Section 4.3.8 - Phthalates

Test with reference to in-house method, determination by GC-MS.

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					002	003+004+005
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	ND	ND
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	ND	ND
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	ND	ND
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	ND	ND
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	ND	ND
Dipentyl phthalate (DPP)	131-18-0	%	0.005	0.1	ND	ND
Di-n-hexyl phthalate (DHP)	84-75-3	%	0.005	0.1	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	ND	ND
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					020	021
Dibutyl phthalate (DBP)	84-74-2	%	0.005	0.1	ND	ND
Benzyl butyl phthalate (BBP)	85-68-7	%	0.005	0.1	ND	ND
Bis (2-ethylhexyl) phthalate (DEHP)	117-81-7	%	0.005	0.1	ND	ND
Di-isononyl phthalate (DINP)	28553-12-0 /68515-48-0	%	0.005	0.1	ND	ND
Diisobutylphthalate (DIBP)	84-69-5	%	0.005	0.1	ND	ND
Dipentyl phthalate (DPP)	131-18-0	%	0.005	0.1	ND	ND
Di-n-hexyl phthalate (DHP)	84-75-3	%	0.005	0.1	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	ND	ND
Conclusion					Pass	Pass

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuvsud.com
Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



8. 16 CFR Part 1303 - Total Lead Content

Test with reference to CPSC-CH-E1003-09.1, determination by ICP-OES

Sample	Unit	MDL	Limit	Result(s)	Conclusion
003+004+005	mg/kg	10.0	90	ND	Pass
020	mg/kg	10.0	90	ND	Pass
021	mg/kg	10.0	90	ND	Pass

9. CPSIA section 101(f) -Total Lead Content (surface coating)

Test with reference to CPSC-CH-E1003-09.1, determination by ICP-OES

Sample	Unit	MDL	Limit	Result(s)	Conclusion
003+004+005	mg/kg	10.0	90	ND	Pass
020	mg/kg	10.0	90	ND	Pass
021	mg/kg	10.0	90	ND	Pass

10. CPSIA section 101(a)(2) - Total Lead Content (Substrate)

Test with reference to CPSC-CH-E1001-08.3 or CPSC-CH-E1002-08.3, determination by ICP-OES

Sample	Unit	MDL	Limit	Result(s)	Conclusion
002	mg/kg	10.0	100	ND	Pass
008	mg/kg	10.0	100	ND	Pass

11. CPSIA, § 108, 16 CFR 1307- Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates

Test with reference to in-house method, determination by GC-MS.

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					002	003+004+005
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	ND	ND
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	ND	ND
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	ND	ND
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	ND	ND
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	ND	ND
Dipentyl phthalate (DPP)	131-18-0	%	0.005	0.1	ND	ND
Di-n-hexyl phthalate (DHP)	84-75-3	%	0.005	0.1	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	ND	ND
Conclusion					Pass	Pass

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.452.24.0258.02A

Date: 2024-10-28



Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					020	021
Dibutyl phthalate (DBP)	84-74-2	%	0.005	0.1	ND	ND
Benzyl butyl phthalate (BBP)	85-68-7	%	0.005	0.1	ND	ND
Bis (2-ethylhexyl) phthalate (DEHP)	117-81-7	%	0.005	0.1	ND	ND
Di-isononyl phthalate (DINP)	28553-12-0 /68515-48-0	%	0.005	0.1	ND	ND
Diisobutylphthalate (DIBP)	84-69-5	%	0.005	0.1	ND	ND
Dipentyl phthalate (DPP)	131-18-0	%	0.005	0.1	ND	ND
Di-n-hexyl phthalate (DHP)	84-75-3	%	0.005	0.1	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	ND	ND
Conclusion					Pass	Pass

-End of Test Report-



Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China