



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Applicant: CAOXIAN PENGHUI ARTS&CRAFTS CO., LTD
Address: NO. 001 NIJI ROAD, CAOXIAN SMALL AND MEDIUM SIZED ENTERPRISE
INCUBATION PARK, HEZE CITY, SHANDONG PROVINCE
Product Name: Kids picnic table & chair set
Model No.: PH24010(3E3-009V00BU)/PH24009(3E3-009V00PK)/PH24009UK(3E3-009V01PK)
Labelled Age Range: Not stated
Age range in testing: Over 3 years
Age Group Assessed As per Age Guideline: Over 3 years
Receipt Date of Sample: 2024-09-23 & 2024-10-21 & 2024-11-07 & 2024-11-26
Date of Testing: 2024-09-23 ~ 2024-09-26 & 2024-10-21 ~ 2024-10-24 & 2024-11-07 ~ 2024-11-12
& 2024-11-26 ~ 2024-11-28
Sample Submitted: The sample(s) was (were) submitted by applicant and identified.
Test Result: Refer to the data listed in following pages

Test Item	Conclusion
1. With reference to EN 71-1:2014+A1:2018 Mechanical and Physical Properties Excluding the requirement of clause 4.2 and 7	Pass
2. With reference to EN 71-2:2020 Flammability	Pass
3. With reference to EN 71-3:2019+A1:2021- Migration of certain elements	Pass
4. With reference to BS EN 71-1:2014+A1:2018 Mechanical and Physical Properties Excluding the requirement of clause 4.2 and 7	Pass
5. With reference to BS EN 71-2:2020 Flammability	Pass
6. With reference to BS EN 71-3:2019+A1:2021- Migration of certain elements	Pass
7. With reference to Regulation (EC) No.1907/2006 (REACH) Annex XVII, Items 51 and 52 - Phthalates Content	Pass
8. BS EN 17191:2021 & EN 17191:2021 Children's Furniture - Seating for children - Safety requirements and test methods	Pass (See remarks)

Remarks: 1. MDL = Method Detection Limit
2. ND = Not Detected (<MDL)
3. ≤ Less than
4. 1 mg/kg = 1 ppm = 0.0001%
5. NA=Not Applicable
6. The client specified the test materials and test items. Conclusion is specific to the tested materials.
7. This report supersedes the previous report 70.452.24.33738.01 dated on 2024-12-13.

Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06



TÜV SÜD Certification and Testing (China) Co., Ltd. Shanghai Branch
Testing Center

Prepared by:

Rainie Dai

Rainie Dai
Reporting Representative



Authorized by:

Neko Ding

Neko Ding
Director

Note:

- (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.
Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question. It does not imply a general statement regarding the quality of products from regular production. For further details please see "Testing, Certification, Validation and Verification Regulations", chapter A-3.3.
For full version, please visit: EN : <https://www.tuvsud.cn/zh-cn/resource/terms-and-conditions---en> ; SCN: <https://www.tuvsud.cn/zh-cn/terms-and-conditions> ; TCN: <https://www.tuvsud.com/zh-tw/terms-and-conditions>
- (2) The results relate only to the Items tested.
- (3) The test report shall not be reproduced except in full without the written approval of the laboratory
- (4) Disclaimer Measurement Uncertainty:
Unless otherwise agreed upon, Pass or Fail verdicts are given based on the measured values without any considerations of measurement uncertainties.
Please note, every test method has a measurement uncertainty which has been evaluated by the laboratory according to ISO/IEC 17025 requirements.
By taking measurement uncertainties into account it might happen that measured values can neither be assessed as Pass nor as Fail.

Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Description of Tested Subject:

Photo



PH24009(3E3-009V00PK)

PH24009UK(3E3-009V01PK)



PH24010(3E3-009V00BU)

Sample	Description
001	Pink coating on wood.(body - PH24009UK)
002	Blue coating on wood.(body - PH24010)
003	Transparent light brown coating on wood.(body - PH24009)
004	Natural color soildwood excluding coatings.(body & umbrella body - PH24009)
005	White woven fabric with four color printings.(umbrella fabric & seat body - PH24009)
006	White sponge.(in the seat - PH24009)
007	White velcro.(hook - PH24009)
008	White velcro.(loop - PH24009)
009	White plastic.(tub - PH24009)
010	Grey soft plastic.(tub -PH24009)

Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Test Result(s):

1. With reference to EN 71-1:2014+A1:2018 Mechanical and Physical Properties

Clause	Requirement	Evaluation
4	General Requirements	
4.1	Material cleanliness	P
4.2	Assembly	#1
4.7	Edges	P
4.8	Points and metallic wires	P
4.9	Protruding parts	P
4.15	Toys intended to bear the mass of a child	P
4.16	Heavy immobile toys	P
6	Packaging	P
7	Warnings and instructions for use	#1

* Abbreviation:

P = Pass

Note:

- Only applicable clauses were shown.

Remark:

#1 = This product is tested as non-toy product, thus Clause 4.2, Clause 7 Warnings, markings and instructions for use was not evaluated.

2. With reference to EN 71-2:2020 Flammability

Clause	Requirement	Evaluation
4.1	General Requirement	P

* Abbreviation:

P = Pass

Note:

- Only applicable clauses were shown.

3. With reference to EN 71-3:2019+A1:2021- Migration of certain elements

Test with reference to EN 71-3:2019+A1:2021, determination by ICP-MS.

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			001	002
Soluble Aluminum	5.00	28130	<5.00	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	<5.00	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	0.055	0.077
Soluble Chromium III	0.04	460	0.055	0.077
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	14.8	12.3



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	64.5	60.8
Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	<5.00	<5.00
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			003	004
Soluble Aluminum	5.00	28130	30.1	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	25.1	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	0.298	<0.04
Soluble Chromium III	0.04	460	0.298	<0.04
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	19.8	6.65
Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	21.9	<5.00
Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	12.8	<5.00
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			005	007
Soluble Aluminum	5.00	28130	<5.00	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	<5.00	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	<0.04	0.165
Soluble Chromium III	0.04	460	<0.04	0.165
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	<5.00	<5.00



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	<5.00	<5.00
Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	<5.00	27.5
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			008	009
Soluble Aluminum	5.00	28130	<5.00	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	<5.00	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	<0.04	<0.04
Soluble Chromium III	0.04	460	<0.04	<0.04
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	<5.00	<5.00
Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	<5.00	<5.00
Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	<5.00	<5.00
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]
			010
Soluble Aluminum	5.00	28130	<5.00
Soluble Antimony	5.00	560	<5.00
Soluble Arsenic	5.00	47	<5.00
Soluble Barium	5.00	18750	<5.00
Soluble Boron	5.00	15000	<5.00
Soluble Cadmium	5.00	17	<5.00
Soluble Chromium	0.04	-	<0.04
Soluble Chromium III	0.04	460	<0.04
Soluble Chromium VI	0.04	0.053	<0.04
Soluble Cobalt	5.00	130	<5.00
Soluble Copper	5.00	7700	<5.00
Soluble Lead	5.00	23	<5.00
Soluble Manganese	5.00	15000	<5.00

Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06



Soluble Mercury	5.00	94	<5.00
Soluble Nickel	5.00	930	<5.00
Soluble Selenium	5.00	460	<5.00
Soluble Strontium	5.00	56000	<5.00
Soluble Tin	2.50	180000	<2.50
Organic Tin	7.50	12	<7.50
Soluble Zinc	5.00	46000	9.81
Conclusion			Pass

4. With reference to BS EN 71-1:2014+A1:2018 Mechanical and Physical Properties

Clause	Requirement	Evaluation
4	General Requirements	
4.1	Material cleanliness	P
4.2	Assembly	#
4.7	Edges	P
4.8	Points and metallic wires	P
4.9	Protruding parts	P
4.15	Toys intended to bear the mass of a child	P
4.16	Heavy immobile toys	P
6	Packaging	P
7	Warnings and instructions for use	#

* Abbreviation:

P = Pass

Note:

- Only applicable clauses were shown.

Remark:

= This product is tested as non-toy product, thus Clause 4.2, Clause 7 Warnings, markings and instructions for use was not evaluated.

5. With reference to BS EN 71-2:2020 Flammability

Clause	Requirement	Evaluation
4.1	General Requirement	P

* Abbreviation:

P = Pass

Note:

- Only applicable clauses were shown.

Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

6. With reference to BS EN 71-3:2019+A1:2021- Migration of certain elements

Test with reference to BS EN 71-3:2019+A1:2021, determination by ICP-MS.

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			001	002
Soluble Aluminum	5.00	28130	<5.00	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	<5.00	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	0.055	0.077
Soluble Chromium III	0.04	460	0.055	0.077
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	14.8	12.3
Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	64.5	60.8
Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	<5.00	<5.00
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			003	004
Soluble Aluminum	5.00	28130	30.1	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	25.1	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	0.298	<0.04
Soluble Chromium III	0.04	460	0.298	<0.04
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	19.8	6.65
Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	21.9	<5.00



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	12.8	<5.00
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			005	007
Soluble Aluminum	5.00	28130	<5.00	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	<5.00	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	<0.04	0.165
Soluble Chromium III	0.04	460	<0.04	0.165
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	<5.00	<5.00
Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	<5.00	<5.00
Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	<5.00	27.5
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]	
			008	009
Soluble Aluminum	5.00	28130	<5.00	<5.00
Soluble Antimony	5.00	560	<5.00	<5.00
Soluble Arsenic	5.00	47	<5.00	<5.00
Soluble Barium	5.00	18750	<5.00	<5.00
Soluble Boron	5.00	15000	<5.00	<5.00
Soluble Cadmium	5.00	17	<5.00	<5.00
Soluble Chromium	0.04	-	<0.04	<0.04
Soluble Chromium III	0.04	460	<0.04	<0.04
Soluble Chromium VI	0.04	0.053	<0.04	<0.04
Soluble Cobalt	5.00	130	<5.00	<5.00
Soluble Copper	5.00	7700	<5.00	<5.00
Soluble Lead	5.00	23	<5.00	<5.00
Soluble Manganese	5.00	15000	<5.00	<5.00
Soluble Mercury	5.00	94	<5.00	<5.00
Soluble Nickel	5.00	930	<5.00	<5.00
Soluble Selenium	5.00	460	<5.00	<5.00
Soluble Strontium	5.00	56000	<5.00	<5.00

Laboratory:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Shanghai Branch, Testing Center
Building B,C, No. 1999 and Building D, No. 2059, Duhui
Road, Minhang District, Shanghai

Phone: +86 21 60376300
Fax: +86 21 60376350
<https://www.tuvsud.com>

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Shanghai Branch, TÜV SÜD Group
Floor 11-12, No 151, Hengtong Road, Jing'an District, Shanghai



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Soluble Tin	2.50	180000	<2.50	<2.50
Organic Tin	7.50	12	<7.50	<7.50
Soluble Zinc	5.00	46000	<5.00	<5.00
Conclusion			Pass	Pass

Parameter	MDL [mg/kg]	Limit [mg/kg]	Result(s) [mg/kg]
			010
Soluble Aluminum	5.00	28130	<5.00
Soluble Antimony	5.00	560	<5.00
Soluble Arsenic	5.00	47	<5.00
Soluble Barium	5.00	18750	<5.00
Soluble Boron	5.00	15000	<5.00
Soluble Cadmium	5.00	17	<5.00
Soluble Chromium	0.04	-	<0.04
Soluble Chromium III	0.04	460	<0.04
Soluble Chromium VI	0.04	0.053	<0.04
Soluble Cobalt	5.00	130	<5.00
Soluble Copper	5.00	7700	<5.00
Soluble Lead	5.00	23	<5.00
Soluble Manganese	5.00	15000	<5.00
Soluble Mercury	5.00	94	<5.00
Soluble Nickel	5.00	930	<5.00
Soluble Selenium	5.00	460	<5.00
Soluble Strontium	5.00	56000	<5.00
Soluble Tin	2.50	180000	<2.50
Organic Tin	7.50	12	<7.50
Soluble Zinc	5.00	46000	9.81
Conclusion			Pass

7. With reference to Regulation (EC) No.1907/2006 (REACH) Annex XVII, Items 51 and 52 - Phthalates Content

Test with reference to in house method, solvent extraction and determination by GC-MS.

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					001+002+003	005
Bis (2-ethylhexyl) phthalate, DEHP	117-81-7	%	0.005	-	<0.005	<0.005
Dibutyl phthalate, DBP	84-74-2	%	0.005	-	0.019	<0.005
Benzyl butyl phthalate, BBP	85-68-7	%	0.005	-	<0.005	<0.005
Diisobutylphthalate, DIBP	84-69-5	%	0.005	-	<0.005	<0.005
Sum of DBP, BBP, DEHP, DIBP	-	%	0.005	0.1	0.019	<0.005
Di-isononyl phthalate, DINP	28553-12-0 /68515-48-0	%	0.005	-	<0.005	<0.005
Di-isodecyl phthalate, DIDP	26761-40-0 /68515-49-1	%	0.005	-	<0.005	<0.005
Di-n-octyl phthalate, DNOP	117-84-0	%	0.005	-	<0.005	<0.005
Sum of DINP, DIDP, DNOP	-	%	0.005	0.1	<0.005	<0.005
Conclusion					Pass	Pass



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					006	007
Bis (2-ethylhexyl) phthalate, DEHP	117-81-7	%	0.005	-	<0.005	<0.005
Dibutyl phthalate, DBP	84-74-2	%	0.005	-	<0.005	<0.005
Benzyl butyl phthalate, BBP	85-68-7	%	0.005	-	<0.005	<0.005
Diisobutylphthalate, DIBP	84-69-5	%	0.005	-	<0.005	<0.005
Sum of DBP, BBP, DEHP, DIBP	-	%	0.005	0.1	<0.005	<0.005
Di-isononyl phthalate, DINP	28553-12-0 /68515-48-0	%	0.005	-	<0.005	<0.005
Di-isodecyl phthalate, DIDP	26761-40-0 /68515-49-1	%	0.005	-	<0.005	<0.005
Di-n-octyl phthalate, DNOP	117-84-0	%	0.005	-	<0.005	<0.005
Sum of DINP, DIDP, DNOP	-	%	0.005	0.1	<0.005	<0.005
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					009	010
Bis (2-ethylhexyl) phthalate, DEHP	117-81-7	%	0.005	-	<0.005	<0.005
Dibutyl phthalate, DBP	84-74-2	%	0.005	-	<0.005	<0.005
Benzyl butyl phthalate, BBP	85-68-7	%	0.005	-	<0.005	<0.005
Diisobutylphthalate, DIBP	84-69-5	%	0.005	-	<0.005	<0.005
Sum of DBP, BBP, DEHP, DIBP	-	%	0.005	0.1	<0.005	<0.005
Di-isononyl phthalate, DINP	28553-12-0 /68515-48-0	%	0.005	-	<0.005	<0.005
Di-isodecyl phthalate, DIDP	26761-40-0 /68515-49-1	%	0.005	-	<0.005	<0.005
Di-n-octyl phthalate, DNOP	117-84-0	%	0.005	-	<0.005	<0.005
Sum of DINP, DIDP, DNOP	-	%	0.005	0.1	<0.005	<0.005
Conclusion					Pass	Pass



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

8. BS EN 17191:2021 & EN 17191:2021 Children's Furniture - Seating for children - Safety requirements and test methods

Item	Requirement-test item	Result, Remark	Evaluation
4	General requirements and test conditions		N/A
4.1	General		N/A
4.5	Seating sizes	Size 2 seating	-
6	General safety requirements		P
6.1	Hazards from glass		P
6.2	Surfaces edges corners and points		P
6.3	Entrapment hazards		P
6.3.1	Finger entrapment hazards		P
6.3.2	Partially bound V and irregular shaped openings		N/A
6.4	Hazards caused by folding of the seating		N/A
6.5	Hazards caused by deckchairs		N/A
6.6	Hazard from moving parts		P
6.6.1	Shearing and compression hazards when setting up and folding		P
6.6.2	Shearing and compression points under influence of powered mechanism		N/A
6.6.3	Shearing and compression points during use		P
6.7	Hazards from enclosure		N/A
6.8	Entanglement hazards		N/A
6.9	Choking and ingestion hazards		N/A
6.9.1	Requirements		N/A
6.9.2	Test methods		-
6.9.3	Filling material		N/A
6.9.4	Magnets		N/A
6.10	Suffocation hazards	Without Plastic sheeting used for packaging with an area greater than 100 mm x 100 mm	N/A
7	Chemicals requirements		P
8	Fire and thermal hazards EN 71-2:2020, 5.5.1 and 5.5.2		P
9	Strength and durability requirements		P
9.1	Test conditions		-
9.2	Seating size and test levels	Sizes 2 seating & Level 1	-
9.3	Requirements		P
9.4	Strength and durability tests		P
9.4.1	General		P
	Seat and back static load test (EN1728:2012,6.4)	Seat force: 750N Back force: 200N Cycles: 10	P
	Seat front edge static load (EN1728:2012,6.5)		N/A
	Foot rest static test (EN1728:2012, 6.8)		N/A
	Arm rest downwards static load test (EN1728:2012, 6.11)		N/A



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

	Seat and back durability test (EN1728:2012,6.17)		N/A
	Seat front edge durability test (EN 1728:2012, 6.18)		N/A
	Arm rest durability test (EN1728:2012, 6.20)		N/A
	Leg forward static load test (EN1728:2012, 6.15)	Seat load: 300N Force: 180N Cycles: 10	P
	Leg sideways static load test (EN1728:2012, 6.16)	Seat load: 300N Force: 180N Cycles: 10	P
	Seat impact test (EN1728:2012, 6.24)	Drop height: 100mm Cycles: 10	P
	Back impact test (EN 1728:2012, 6.25)	Drop height: 70mm Cycles: 10	P
9.4.2	Soft seating		N/A
9.4.3	Seating intended for very young children only		N/A
10	Stability requirements		P
10.1	General		P
	Forward overturning (EN 1022:2018, 7.3.1 and 7.3.2)	Seat force: 250N Horizontal force: 20N	P
	Corner stability (EN 1022:2018, 7.3.3)		N/A
	Sideways stability without arms (EN 1022:2018, 7.3.4)	Seat force: 250N Horizontal force: 20N	P
	Sideways stability with armrests (EN 1022:2018, 7.3.5)		N/A
	Rearwards stability (EN 1022:2018, 7.3.6)		N/A
10.2	Alternative rearwards stability tests for rocking and reclining chairs		N/A
10.2.1	Rocking chairs		N/A
10.2.2	Reclining chairs		N/A
10.2.3	Summary		N/A
11	Product information		P
11.1	General		P
11.2	Marking		P
11.2.1	Requirements		P
11.2.2	Durability of marking		P
11.2.2.1	Requirement		P
11.2.2.2	Test method		-
11.3	Purchase information		P
11.4	Instructions for use		P
11.4.1	General		P
11.4.2	Warnings		P
11.4.3	Additional information		P

Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Abbreviation: P=Pass; F=Fail; N/A = Not Applicable; N/T=Not Tested; N/R=Not Requested

Remark:

1. The sample has been examined according to the requirements described in the product standard.
2. Only the English required information presence were verified as per standard, it is vendor's responsibility to ensure the facticity of the information.
3. Sample A, B&C share the same structure except for the colour, and the test was conducted on the sample A.
4. Only physical test of the seating of sample A was checked according to the client's requirement.

Description of Tested Subject:

1	Product Description	Kids picnic table & chair set
2	Dimensions / Weight	D278 x W899 x H276/315 (mm)/2.70 (kg)
3	Test level	1
Sample A		
Front view		Side view
		

Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06



Bottom view	Set view
	

Sample B	Sample C
Set view	Set view
	



Test Report

No.: 70.452.24.33738.01R1

Date: 2025-01-06

Attachment:

The same material information is based on the guarantee letter provided by the client.

Sample	Description	Same Material Model No.
001	Pink coating on wood.(body - PH24009UK)	PH24009
003	Transparent light brown coating on wood.(body - PH24009)	PH24009UK & PH24010
004	Natural color soildwood excluding coatings.(body & umbrella body - PH24009)	PH24009UK & PH24010
005	White woven fabric with four color printings.(umbrella fabric & seat body - PH24009)	PH24009UK
006	White sponge.(in the seat - PH24009)	PH24010
007	White velcro.(hook - PH24009)	PH24010
008	White velcro.(loop - PH24009)	PH24010
009	White plastic.(tub - PH24009)	PH24009UK & PH24010
010	Grey soft plastic.(tub -PH24009)	PH24009UK & PH24010

-End of Test Report-