

TEST REPORT

<u>Applicant</u>	: Zhejiang Taixing Kid Toy CO., LTD
<u>Address</u>	: B-2 Jiaoyang Industry Zone, Taishun, Wenzhou City, Zhejiang, China
<u>Sample description</u>	: Kids Kitchen Playset
<u>Item no.</u>	: 350-217V80WT 350-217V80PK 350-213V80WW 350-214V80WT
<u>Country of origin</u>	: China
<u>Age requested on application form</u>	: 3+
<u>Labelled age grade</u>	: 3+
<u>Age grade applied in testing</u>	: Over 3 Years
<u>Lab recommended age grade</u>	: Over 3 Years
<u>Sample received date</u>	: 10-Apr-2026
<u>Further information date</u>	: 13-May-2026
<u>Turn around time</u>	: 10-Apr-2026 To 14-May-2026

The following test item(s) was/were performed on selected sample(s) and/or component(s) confirmed by applicant



TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Total Lead Content in Metal	SOR/2018-83, Consumer Products Containing Lead Regulations	Pass
Total Lead Content in Coating	SOR/2018-83, Consumer Products Containing Lead Regulations	Pass
Total Lead Content in Plastic	SOR/2018-83, Consumer Products Containing Lead Regulations	Pass
Physical and Mechanical Hazards	ASTM F963-23	Pass
Flammability of Toys	ASTM F963-23, Section 4.2	Pass
Heavy Metals	ASTM F963-23, Section 4.3.5	Pass
Phthalates Content	ASTM F963-23, Section 4.3.8	Pass
Physical and Mechanical Hazards	CPSC Regulations	Pass
Flammability Test	CPSC Regulations-1500.3(c)(6)(vi)	Pass
Total Lead Content in Paint and Similar Surface-coating Materials	US 16 CFR 1303	Pass
Phthalates Content	CPSC 16 CFR part 1307	Pass
Total Lead Content in Substrate	US CPSIA, Section 101 (15 U.S.C. § 1278a)	Pass
Phthalates Content	US CPSIA, Section 108	Pass
Total Lead Content in Paint / Surface Coating	US CPSIA, Section 101 (15 U.S.C. § 1278a)	Pass
Tracking Label Assessment	US CPSIA, Section 103	Pass
Phthalates Content	US California Proposition 65	Pass
Total Lead Content	US California Proposition 65	Pass
Small Parts	CPSC Regulations-16 CFR 1501	Not Applicable
Mechanical and Physical Properties	SOR/2011-17	Pass
Flammability of Toys	SOR/2011-17	Pass
Heavy Metal in Stickers, Films and Surface Coating Materials	SOR/2011-17	Pass
Heavy Metals in Plastic Materials	SOR/2011-17	Not Applicable
Phthalate Regulations	SOR/2016-188	Pass
Surface Coating Materials Regulations	SOR/2016-193	Pass

Eurofins (Shanghai) contact information**Customer service:** Ruby.Li@cpt.eurofinscn.com+86 21 23509759 #9759**Sales specialist:** Sophia.Ma@cpt.eurofinscn.com

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.



Ada Jin
Toy Division Assistant Manager


SAMPLE PHOTO(S)



EFW526041540-CG-01

TO BE CONTINUED

SAMPLE PHOTO(S)



EFW526041540-CG-01

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Sample No.
1	White coating on wood	A,B,C,D
2	White coating on plastic	A,B,C
3	Gold coating on plastic (knob)	A,D
4	Pink coating on plastic (edge sealing)	B
5	Pink coating on wood	B
6	Silver coating on plastic (knob)	B
7	Light grey coating on wood (range hood body)	B
8	Dark grey coating on wood (faucet)	C
9	Grey coating on wood	A,C
10	Gold coating on wood	A,D
11	Silver coating on wood	A,B,D
12	Silver coating on plastic (edge sealing)	A
13	Brown coating on wood (coffee bean)	A,B
14	Light grey coating on wood (coffee bean)	A,B
15	Grey coating on wood	D
16	Light grey coating on wood	D
17	White paper with white/grey coating (background wall)	A
18	Multi-color coating on wood	A
19	White paper with multi-color coating (background wall)	B
20	White paper with white coating	A,B,C
21	Multi-color coating on wood	C
22	Multi-color coating on wood	B
23	Beige/dark beige coating on wood	C
24	Beige/dark beige coating on plastic (edge sealing)	C
25	Beige/light brown coating on wood	A,B,D
26	Beige/light brown coating on plastic (edge sealin)	A,B,D
27	Dark grey plastic (knob)	C
28	Transparent plastic (cabinet door)	A,B,C,D
29	Beige plastic excluding coating (edge sealin)	A,B,C,D
30	Beige plastic (slide rail)	C
31	Black plastic	C
32	White plastic (big screw)	C
33	White plastic (basin)	A,B,C,D
34	Light grey plastic (hook)	C
35	Beige plastic (cube)	A,B,C,D
36	Beige plastic excluding coating (knob/handle)	A,D
37	Dark grey plastic (water dispenser)	A,B,D
38	Transparent plastic (cup)	A,B,D
39	Semi-transparent plastic (ice cubes)	A,B
40	White plastic excluding coating (seal edges)	A,B
41	Grey plastic excluding coating (faucet)	A,D
42	Semi-transparent plastic (buckle)	A,B,D
43	White plastic (plate/cup)	B,D
44	Beige white plastic	B
45	Beige white plastic (handle)	B
46	Grey plastic excluding coating (door handles/faucets/knob)	B,C
47	Light brown plastic excluding coating (cup/plate)	A

TO BE CONTINUED

Component No.	Component	Sample No.
48	Black plastic excluding coating (door handle)	D
49	Black plastic (stove)	D
50	Red plastic (stove)	D
51	White plastic excluding coating (hook)	D
52	Brown MDF wood excluding coating	A,B,C,D
53	Natural color wood excluding coating	A,B,C,D
54	Silver metal (pot)	B,C
55	Silver metal (shovel/spoon)	B,C
56	Silver metal (screw/iron sheet)	A,B,C,D
57	Silver metal (hook)	A,B
58	Gold coated metal (spoon/shovel)	A,D
59	Gold coated metal (pot)	A,D

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

E-mail: info.shmts@cpt.eurofinscn.com

Website: www.eurofins.cn

TEST RESULT

Total Lead Content in Metal

Test Request: Lead content as specified in Canada Consumer Product Safety Act – Consumer Products Containing Lead Regulations, SOR/2018-83.

Test Method: With reference to Product Safety Laboratory, Reference Manual, Book 5 - Laboratory Policies and Procedures, Part B: Test Methods Section, Method C02.4.1-2019, analysis is performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				54+55	56+57	58	59
Lead (Pb)	mg/kg	90	10	ND	ND	ND	ND

Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

Exception:

Each accessible part may contain more than 90 mg/kg of lead if

- a) lead is necessary to produce an essential characteristic of the part;
- b) no alternative part containing less lead is available; and
- c) the part, when tested in accordance with good laboratory practices, does not release more than 90 mg/kg of lead.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

E-mail: info.shmts@cpt.eurofinscn.com

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Website: www.eurofins.cn

TEST RESULT

Total Lead Content in Coating

Test Request: Lead content as specified in Canada Consumer Product Safety Act – Consumer Products Containing Lead Regulations, SOR/2018-83.

Test Method: With reference to Product Safety Laboratory, Reference Manual, Book 5 - Laboratory Policies and Procedures, Part B: Test Methods Section, Method C02.2.2-2024, analysis is performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				1+2+3	4+5+6	7+8+9	10+11
Total Lead	mg/kg	90	10	ND	ND	ND	16

Test Item(s)	Unit	Limit	MDL	Result			
				13+14	15+16	19	20
Total Lead	mg/kg	90	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				21	22	23	24
Total Lead	mg/kg	90	10	ND	19	ND	ND

Test Item(s)	Unit	Limit	MDL	Result	
				25	26
Total Lead	mg/kg	90	10	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

Exception:

Each accessible part may contain more than 90 mg/kg of lead if

a) lead is necessary to produce an essential characteristic of the part;

b) no alternative part containing less lead is available; and

c) the part, when tested in accordance with good laboratory practices, does not release more than 90 mg/kg of lead.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

E-mail: info.shmts@cpt.eurofinscn.com

Website: www.eurofins.cn

TEST RESULT

Total Lead Content in Plastic

Test Request: Lead content as specified in Canada Consumer Product Safety Act – Consumer Products Containing Lead Regulations, SOR/2018-83.

Test Method: With reference to Product Safety Laboratory, Reference Manual, Book 5 - Laboratory Policies and Procedures, Part B: Test Methods Section, Method C02.3.2-2021, analysis is performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				27+28+29	30+31+32	33+34+35	36+37+38
Total Lead	mg/kg	90	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				39+40+41	42+43+44	45+46	48+49
Total Lead	mg/kg	90	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result	
				50+51	52+53
Total Lead	mg/kg	90	10	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

Exception:

Each accessible part may contain more than 90 mg/kg of lead if

- a) lead is necessary to produce an essential characteristic of the part;
- b) no alternative part containing less lead is available; and
- c) the part, when tested in accordance with good laboratory practices, does not release more than 90 mg/kg of lead.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Physical and Mechanical Hazards

Test Request: As specified in Consumer Safety Specification ASTM F963-23
Test Sample: C,A,B

Section	Description	Result
4.1	Material Quality	P
4.3.7	Stuffing Materials	N/A
4.5	Sound-Producing Toys	N/A
4.6	Small Objects	N/A
4.6.1	Toys that are intended for children under 36 months of age	N/A
4.6.2	Mouth-Actuated Toys	N/A
4.6.3	Toys that are intended for children over 36 months but less than 72 months	N/A
4.7	Accessible Edges	P
4.8	Projections	N/A
4.8.1	Bath Toy Projections	N/A
4.9	Accessible Points	P
4.10	Wires or Rods	N/A
4.11	Nails and Fasteners	P
4.12	Plastic Film	N/A
4.13	Folding Mechanisms and Hinges	P
4.14	Cords, Straps and Elastics	N/A
4.15	Stability and Over-Load Requirements	P
4.16	Confined Spaces	P
4.17	Wheels, Tires, and Axles	N/A
4.18	Holes, Clearances, and Accessibility of Mechanisms	N/A
4.19	Simulated Protective Devices	N/A
4.20	Pacifiers	N/A
4.21	Projectile Toys	N/A
4.22	Teethers and Teething Toys	N/A
4.23	Rattles	N/A
4.24	Squeeze Toys	N/A
4.25	Battery-Operated Toys (exclude section 4.25.9 Battery-powered ride-on toys and section 4.25.10 Toys contain secondary cells or secondary batteries)	N/A
4.26	Toys Intended to be Attached to a Crib or Playpen	N/A
4.27	Stuffed and Beanbag-Type Toys	N/A
4.28	Stroller and Carriage Toys	N/A
4.30	Toy Gun Marking	N/A
4.31	Balloons	N/A
4.32	Certain Toys with Nearly Spherical Ends	N/A
4.33	Marbles	N/A
4.34	Balls	N/A
4.35	Pompoms	N/A
4.36	Hemispheric-Shaped Objects	N/A
4.37	Yo Yo Elastic Tether Toys	N/A

TO BE CONTINUED

TEST RESULT

Section	Description	Result
4.38	Magnets	N/A
4.39	Jaw Entrapment in Handles and Steering Wheels	N/A
4.40	Expanding Materials	N/A
4.41	Toy Chests	N/A
5	Labeling Requirements	
5.1	Federal Government Requirements	P
5.2	Age Grading Labeling	P
5.3	Safety Labeling Requirements	P
5.4	Aquatic Toys	N/A
5.5	Crib and Playpen Toys	N/A
5.6	Mobiles	N/A
5.7	Stroller and Carriage Toys	N/A
5.8	Toys Intended to be Assembled by an Adult	P
5.9	Simulated Protective Devices	N/A
5.10	Toys with Functional Sharp Edges or Points	N/A
5.11	Small Objects, Small Balls, Marbles and Balloons	N/A
5.12	Art Materials	N/A
5.13	Electric Toys	N/A
5.14	Battery-Operated Toys	N/A
5.14.1	Battery-Powered Ride-On Toys	N/A
5.14.2	Button or Coin Cell Batteries	N/A
5.15	Promotional Materials	P
5.16	Magnets	N/A
6	Instructional Literature	
6.1	Definition and Description	P
6.2	Crib and Playpen Toys	N/A
6.3	Mobiles	N/A
6.4	Toys Intended to be Assembled by an Adult	P
6.5	Battery-Operated Toys	N/A
6.6	Battery Powered Ride-On Toys	N/A
6.7	Toys in Contact with Food	N/A
6.8	Toy Chests	N/A
6.9	The instructional material for toys which require a manufacturer-supplied specialty or custom tool to access the battery (ies)	N/A
7	Producer's Markings	
7.1	Producer's or Distributor's Name and Address	P
7.2	Battery-Powered Ride-on Toys	N/A
7.3	Toy Chests	N/A

Remark:

P-Pass, F- Fail, N/A-Not Applicable, N/C-Not conduct as per client's request

TO BE CONTINUED

TEST RESULT

Flammability of Toys

Test Request: As specified in ASTM F963-23, Section 4.2, testing procedure for materials other than textiles (excluding paper) used in toys is contained in Annex A5.

Sample	Limit	Result
A	0.1 inch/second	P
B	0.1 inch/second	P
C	0.1 inch/second	P

Remark:

P-Pass, F- Fail, N/A-Not Applicable

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.
Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

E-mail: info.shmts@cpt.eurofinscn.com

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Website: www.eurofins.cn

TEST RESULT

Heavy Metals

ASTM F963-23- Heavy Elements – Total Lead in Paint and Similar Surface-Coating Material (Clause 4.3.5.1(1))
Test Method: ASTM International Standard ASTM F963-23, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				6	7	8	9	10
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				11	12	13	14	17
Total Lead in Paint	mg/kg	90	10	32	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				18	19	20	21	22
Total Lead in Paint	mg/kg	90	10	21	ND	ND	ND	19

Tested Item(s)	Unit	Limit	MDL	Result			
				23	24	25	26
Total Lead in Paint	mg/kg	90	10	ND	ND	ND	ND

ASTM F963-23- Heavy Elements – Total Lead in Substrate Material (Clause 4.3.5.2(2) (a))
Test Method: ASTM International Standard ASTM F963-23, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				27	28	29	30	31
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				32	33	34	35	36
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				37	38	39	40	41
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				42	43	44	45	46
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				47	52	53	54	55
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result			
				56	57	58	59
Total Lead in Substrate	mg/kg	100	10	ND	ND	ND	ND

ASTM F963-23- Heavy Elements – Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay (Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-23, Section 8.3.2 to 8.3.5 (excluding 8.3.5.5(3))

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				6	7	8	9	10
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				11	12	13	14	17
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	15	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result				
				18	19	20	21	22
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				23	24	25	26	27
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				28	29	30	31	32
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				33	34	35	36	37
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result				
				38	39	40	41	42
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				43	44	45	46	47
Soluble Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND	ND
Soluble Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND	ND	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result	
				52	53
Soluble Antimony	mg/kg	60	5	ND	ND
Soluble Arsenic	mg/kg	25	2.5	ND	ND
Soluble Barium	mg/kg	1000	10	23	ND
Soluble Cadmium	mg/kg	75	5	ND	ND
Soluble Chromium	mg/kg	60	5	ND	ND
Soluble Lead	mg/kg	90	5	ND	ND
Soluble Mercury	mg/kg	60	5	ND	ND
Soluble Selenium	mg/kg	500	10	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

The analytical results were adjusted by subtracting analytical correction factor.

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content in Toys (including pacifiers, rattles, and teethers) Material (ASTM F963-23, Section 4.3.8)

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+ 3	4+5+ 6	7+8+ 9	10+1 1+12
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					13+1 4	17	18	19
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	0.08 0
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					20	21	22	23
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					24	25	26	27+28+29
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					30+3 1+32	33+3 4+35	36+3 7+38	39+4 0+41
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					42+43+44	45+46+47
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND

Remarks:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

E-mail: info.shmts@cpt.eurofinscn.com

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Website: www.eurofins.cn

TEST RESULT

Physical and Mechanical Hazards

Test Request: The Mechanical Hazards Requirements of 16 CFR 1500, after Use and Abuse Tests.
Test Sample: C,A,B

Section	Description	Result
16 CFR 1501	Small Parts	N/A
16 CFR 1500.48	Sharp Points	P
16 CFR 1500.49	Sharp Edges	P
16 CFR 1510	Rattles	N/A
16 CFR 1511	Pacifier	N/A

Remark:

The use and abuse tests conducted are:

As Received & Normal Use (1500.50)

Impact Test (1500.53(b))

Torque Test (1500.53(e))

Tension Test (1500.53(f))

P - Pass, N/A - Not Applicable

Flammability Test

Test Request: As per U.S. code of federal regulations title 16 CFR 1500.3(c)(6)(vi) for flammable solid, tested by the method described in 16 CFR 1500.44.

Sample	Limit	Result
A	0.1 inch/second	P
B	0.1 inch/second	P
C	0.1 inch/second	P

Remark:

P - Pass; F - Fail; NA - Not Applicable

TO BE CONTINUED

TEST RESULT

Total Lead Content in Paint and Similar Surface-coating Materials

Test Request: Total lead content as specified in US 16 CFR 1303

Test Method: CPSC-CH-E1003-09.1

The sample was acid digested, and total lead content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				1+2+3	4+5+6	7+8+9	10+11+12
Total Lead (Pb)	mg/kg	90	10	ND	ND	ND	11.0

Test Item(s)	Unit	Limit	MDL	Result			
				13+14	17	18	19
Total Lead (Pb)	mg/kg	90	10	ND	ND	21	ND

Test Item(s)	Unit	Limit	MDL	Result			
				20	21	22	23
Total Lead (Pb)	mg/kg	90	10	ND	ND	19	ND

Test Item(s)	Unit	Limit	MDL	Result		
				24	25	26
Total Lead (Pb)	mg/kg	90	10	ND	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates as specified in CPSC 16 CFR part 1307.

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+ 3	4+5+ 6	7+8+ 9	10+1 1+12
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					13+1 4	17	18	19
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	0.08 0
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					20	21	22	23
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					24	25	26	27+28+29
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					30+3 1+32	33+3 4+35	36+3 7+38	39+4 0+41
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					42+43+44	45+46+47
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Di-pentyl phthalate (DPP)	131-18-0	%	0.1	0.005	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND

Remarks:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

E-mail: info.shmts@cpt.eurofinscn.com

Website: www.eurofins.cn

TEST RESULT

Total Lead Content in Substrate

Test Request: Total lead in substrate as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101 (15 U.S.C. § 1278a).

Test Method: CPSC-CH-E1001-08.3 for metal product, CPSC-CH-E1002-08.3 for nonmetal product. The sample was acid digested, and total lead content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				27+28+29	30+31+32	33+34+35	36+37+38
Total Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				39+40+41	42+43+44	45+46+47	52+53
Total Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				54+55	56+57	58	59
Total Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 108

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+ 3	4+5+ 6	7+8+ 9	10+1 1+12
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					13+1 4	17	18	19
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	0.08 0
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

E-mail: info.shmts@cpt.eurofinscn.com

Website: www.eurofins.cn

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					20	21	22	23
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					24	25	26	27+28+29
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					30+31+32	33+34+35	36+37+38	39+40+41
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					42+43+44	45+46+47
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND

Remarks:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Total Lead Content in Paint / Surface Coating

Test Request: Total lead in paint/ similar surface coatings as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101 (15 U.S.C. § 1278a).

Test Method: CPSC-CH-E1003-09.1
The sample was acid digested, and total lead content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				1+2+3	4+5+6	7+8+9	10+11+12
Total Lead (Pb)	mg/kg	90	10	ND	ND	ND	11.0

Test Item(s)	Unit	Limit	MDL	Result			
				13+14	17	18	19
Total Lead (Pb)	mg/kg	90	10	ND	ND	21.0	ND

Test Item(s)	Unit	Limit	MDL	Result			
				20	21	22	23
Total Lead (Pb)	mg/kg	90	10	ND	ND	19.0	ND

Test Item(s)	Unit	Limit	MDL	Result		
				24	25	26
Total Lead (Pb)	mg/kg	90	10	ND	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

E-mail: info.shmts@cpt.eurofinscn.com

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Website: www.eurofins.cn

TEST RESULT

Tracking Label Assessment

Test Request: As per Consumer Product Safety Improvement Act (CPSIA) 2008 section 103 tracking labels for children products
Test Sample: C,A,B

Labeling Content	Observation Result	Location	Conclusion
Name of Manufacturer/ Import / Private Labeler in the tracking label	Present	Packaging Product	Pass
Location of production	Present	Packaging Product	Pass
Date of production	Present	Packaging Product	Pass
Cohort information (including the batch, run number, or other identifying characteristic)	Present	Packaging Product	Pass

Remark:

The tracking label assessment was based on the submitted sample and the information provided by the applicant. There was no verification on the validity of such information.

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content as specified in US California Proposition 65

Test Method: EPA 3550C:2007, EPA 8270E:2018, solvent extraction and quantification by GC-MS.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+ 3	4+5+ 6	7+8+ 9	10+1 1+12
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					13+1 4	17	18	19
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	0.08 0
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					20	21	22	23
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					24	25	26	27+28+29
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					30+31+32	33+34+35	36+37+38	39+40+41
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					42+43+44	45+46+47
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND

Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

The limit(s) was/were referred from various court cases. Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

TO BE CONTINUED

TEST RESULT

Total Lead Content

Test Request: Total lead content as specified in US California Proposition 65.

Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996, acid digestion/ microwave digestion method was used, analysis was performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				27+28+29	30+31+32	33+34+35	36+37+38
Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				39+40+41	42+43+44	45+46+47	52+53
Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				54+55	56+57	58	59
Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

The limit(s) was/were referred from various court cases. Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Total Lead Content

Test Request: Total lead content as specified in US California Proposition 65.

Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996, acid digestion/ microwave digestion method was used, analysis was performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				1+2+3	4+5+6	7+8+9	10+11+12
Lead (Pb)	mg/kg	90	10	ND	ND	ND	11

Test Item(s)	Unit	Limit	MDL	Result			
				13+14	17	18	19
Lead (Pb)	mg/kg	90	10	ND	ND	21	ND

Test Item(s)	Unit	Limit	MDL	Result			
				20	21	22	23
Lead (Pb)	mg/kg	90	10	ND	ND	19	ND

Test Item(s)	Unit	Limit	MDL	Result		
				24	25	26
Lead (Pb)	mg/kg	90	10	ND	ND	ND

Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

The limit(s) was/were referred from various court cases. Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Mechanical and Physical Properties

Test Request: As specified in the mechanical hazards requirements of the tested sections of Canada Consumer Product Safety Act Schedule 2, and Toys Regulations SOR/2011-17 latest amended by SOR/2024-217

Test Sample: C,B,D

Section	Description	Result
	General	
3	Official languages	N/A
	Packaging	
4	Flexible film bag	N/A
	Electrical Hazards	
5	Electrically operated toys	N/A
6	Electrically heated toys	N/A
	Mechanical Hazards	
7	Small parts	N/A
8	Metal edges	P
9	Wire frames	N/A
10	Plastic edges	P
11	Wood	P
12	Glass	N/A
13	Fasteners	P
14	Safety stops or locking devices	N/A
15	Spring-wound driving mechanisms	N/A
16	Projectile components	N/A
17	Enclosures	N/A
18	Stability	P
	Auditory Hazards	
19	Decibel limit	N/A
	Thermal and Flammability Hazards	
20	Heated surfaces, parts or substances	N/A
	Specific Products	
28	Dolls, plush toys and soft toys - fastenings	N/A
29(a)(b)	Dolls, plush toys and soft toys - stuffing	N/A
30	Dolls, plush toys and soft toys - small parts	N/A
31	Dolls, plush toys and soft toys - eyes and noses	N/A
35	Plant seeds - noise	N/A
36	Plant seeds - stuffing material	N/A
37	Pull and push toys - shaft-like handles	N/A
38	Toys steam engines - boilers – safety valves	N/A
39	Finger paints - water-based paints	N/A
40	Rattles - construction	N/A
41	Elastics - length or extensibility	N/A
42	Yo-Yo type balls - stretchable cord	N/A
43	Magnetic Toys - Magnetic Force	N/A
44	Magnetic Toys - Exceptions	N/A

TO BE CONTINUED

TEST RESULT

Section	Description	Result
45	Toys Intended to be Entered by a Child - Exception	N/A
47	Toys Intended to be Entered by a Child - Warning	N/A
	Canada Consumer Product Safety Act, Schedule 2	
1	Jequirity Beans	P
2	Spectacle frames contain cellulose nitrate	N/A
3	Baby Walkers	N/A
5	Structural devices that position feeding bottles to allow babies to feed themselves from the bottle while unattended	N/A
8	Kites	N/A
9	Kite strings	N/A
14	Lawn, darts with elongated tips	N/A

Remark:

P – Pass, F – Fail, NA – Not Applicable, NC – Not Conduct as per client's request

Flammability of Toys

Test Request: As specified in the flammability requirements of the tested sections of Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 latest amended by SOR/2024-217.
Test Sample: C,B,D

Section	Description	Result
21	Celluloid or cellulose nitrate	P
32	Doll, plush toy and soft toy - Flammability of outer covering	N/A
33	Doll, plush toy and soft toy - Flammability of yarn	N/A
34	Doll, plush toy and soft toy - Flammability of hair or mane	N/A
46(1)	Toys Intended to be Entered by a Child - Requirements and testing	N/A

Remark:

P – Pass, F – Fail, NA – Not Applicable, NC – Not Conduct as per client's request

TO BE CONTINUED

TEST RESULT

Heavy Metal in Stickers, Films and Surface Coating Materials

Test Request: Heavy metal in stickers, films and surface coating materials as specified in Canada Consumer Product Safety Act - Toys Regulations, SOR/2011-17 latest amended by SOR/2024-217 Section 23.

Test Method: With reference to Product Safety Laboratory, Reference Manual, Book 5 – Laboratory Policies and Procedures, Part B: Test Methods Section, Method C02.2.2-2024, Method C08.1-2022.

Test Item(s)	Unit	Limit	MDL	Result			
				1	2	3	4
Total Lead	mg/kg	90	10	ND	ND	ND	ND
Total Mercury	mg/kg	10	1	ND	ND	ND	ND
Soluble Antimony	mg/kg	1000	5	ND	ND	ND	ND
Soluble Arsenic	mg/kg	1000	2.5	ND	ND	ND	ND
Soluble Cadmium	mg/kg	1000	5	ND	ND	ND	ND
Soluble Selenium	mg/kg	1000	10	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				5	6	7	8
Total Lead	mg/kg	90	10	ND	ND	ND	ND
Total Mercury	mg/kg	10	1	ND	ND	ND	ND
Soluble Antimony	mg/kg	1000	5	ND	ND	ND	ND
Soluble Arsenic	mg/kg	1000	2.5	ND	ND	ND	ND
Soluble Cadmium	mg/kg	1000	5	ND	ND	ND	ND
Soluble Selenium	mg/kg	1000	10	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				9	10	11	13
Total Lead	mg/kg	90	10	ND	ND	32.0	ND
Total Mercury	mg/kg	10	1	ND	ND	ND	ND
Soluble Antimony	mg/kg	1000	5	ND	ND	ND	ND
Soluble Arsenic	mg/kg	1000	2.5	ND	ND	ND	ND
Soluble Cadmium	mg/kg	1000	5	ND	ND	ND	ND
Soluble Selenium	mg/kg	1000	10	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				14	15	16	19
Total Lead	mg/kg	90	10	ND	ND	ND	ND
Total Mercury	mg/kg	10	1	ND	ND	ND	ND
Soluble Antimony	mg/kg	1000	5	ND	ND	ND	ND
Soluble Arsenic	mg/kg	1000	2.5	ND	ND	ND	ND
Soluble Cadmium	mg/kg	1000	5	ND	ND	ND	ND
Soluble Selenium	mg/kg	1000	10	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	15.0	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	Unit	Limit	MDL	Result			
				20	21	22	23
Total Lead	mg/kg	90	10	ND	ND	19.0	ND
Total Mercury	mg/kg	10	1	ND	ND	ND	ND
Soluble Antimony	mg/kg	1000	5	ND	ND	ND	ND
Soluble Arsenic	mg/kg	1000	2.5	ND	ND	ND	ND
Soluble Cadmium	mg/kg	1000	5	ND	ND	ND	ND
Soluble Selenium	mg/kg	1000	10	ND	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result		
				24	25	26
Total Lead	mg/kg	90	10	ND	ND	ND
Total Mercury	mg/kg	10	1	ND	ND	ND
Soluble Antimony	mg/kg	1000	5	ND	ND	ND
Soluble Arsenic	mg/kg	1000	2.5	ND	ND	ND
Soluble Cadmium	mg/kg	1000	5	ND	ND	ND
Soluble Selenium	mg/kg	1000	10	ND	ND	ND
Soluble Barium	mg/kg	1000	10	ND	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.

Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

E-mail: info.shmts@cpt.eurofinscn.com

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Website: www.eurofins.cn

TEST RESULT

Phthalate Regulations

Test Request: Phthalates Content as specified in Canada Consumer Product Safety Act - Phthalate Regulations, SOR/2016-188.

Test Method: With reference to Product Safety Laboratory, Reference Manual, Book 5 – Laboratory Policies and Procedures, Part B: Test Methods Section, Method C34.2-2018, analysis is performed by GC-MS.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1+2+ 3	4+5+ 6	7+8+ 9	10+1 1
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Phthalic acid, bis-iso-decyl ester (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					13+1 4	15+1 6	19	20
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.08 0	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Phthalic acid, bis-iso-decyl ester (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					21	22	23	24
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Phthalic acid, bis-iso-decyl ester (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					25	26	27+28+29	30+31+32
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Phthalic acid, bis-iso-decyl ester (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					33+34+35	36+37+38	39+40+41	42+43+44
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Phthalic acid, bis-iso-decyl ester (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND

TO BE CONTINUED

TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					45+46	48+49	50+51
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Phthalic acid, bis-iso-decyl ester (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND

Remarks:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

DEHP, DBP and BBP are restricted for the vinyl in a toy or child care article. DINP, DIDP and DNOP are restricted for the vinyl in any part of a toy or child care article that can, in a reasonably foreseeable manner, be placed in the mouth of a child under four years of age.

TO BE CONTINUED

TEST RESULT

Surface Coating Materials Regulations

Test Request: Total lead and mercury in surface coatings as specified in Canada Consumer Product Safety Act, Surface Coating Materials Regulations, SOR/2016-193 latest amended by SOR/2022-122.

Test Method: With reference to Product Safety Laboratory, Reference Manual, Book 5 - Laboratory Policies and Procedures, Part B: Test Methods Section, Method C02.2.1-2018, C02.2.2-2024.

Test Item(s)	Unit	Limit	MDL	Result			
				1+2+3	4+5+6	7+8+9	10+11
Lead (Pb)	mg/kg	90	10	ND	ND	ND	11.0
Total Mercury	mg/kg	10	1	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				13+14	15+16	19	20
Lead (Pb)	mg/kg	90	10	ND	ND	ND	ND
Total Mercury	mg/kg	10	1	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				21	22	23	24
Lead (Pb)	mg/kg	90	10	ND	19.0	ND	ND
Total Mercury	mg/kg	10	1	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result	
				25	26
Lead (Pb)	mg/kg	90	10	ND	ND
Total Mercury	mg/kg	10	1	ND	ND

Remark:

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

This test report is governed by the Terms and Conditions, available on request or accessible at <https://www.eurofins.cn/consumer-product-testing/general-terms/>. Attention is especially drawn to the limitations of liability, indemnification and jurisdictional provisions defined therein. This report is issued strictly based on the testing of the samples submitted by you. The test results in this report refer only to the sample(s) actually tested and do not refer or be deemed to refer to any bulk production from which such sample(s) may be said to have been obtained. In the event that Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd. ("ERF") was requested to survey and test any bulk production quantity of samples, ERF, in the absence of any contrary written instructions, performed random sampling of bulk production for testing purposes. Variations in the conditions under which samples are stored, transported, etc., may lead to variations in the test results. ERF cannot anticipate and shall not be held responsible for variations in test results that may be due to factors beyond ERF's control, such as, sample cross-contamination, evaporation of volatile substances due to storage temperature, humidity, etc. This report does not constitute a recommendation, actual or implied, for any specific course of action. Other than the expressed warranties made in the Terms and Conditions of the ERF Test Request Form, ERF makes no warranties or representations either express or implied with respect to this report. In no circumstances whatsoever shall ERF be liable for any consequential, special or incidental damages arising out of, or in connection with, this report. This document shall not be reproduced except in full unless prior written authorization from ERF has been attained. Unless otherwise stated from the customer, regulation or the standard specification, Eurofins will apply it in accordance with ILAC G8:09/2019 (binary statement for simple acceptance rule) and shared risk decision rule. If you happen to have any complaints, please do it by sending email to info.shmts@cpt.eurofinscn.com and referring to this report number. As per regulation of China Metrology Accreditation (CMA), a report without CMA accreditation logo will not serve as testimonial to the public for the purpose defined by CMA regulations.

END OF THE REPORT

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd.
Building 1, No. 105, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Tel: (86) 21-2350 9600

E-mail: info.shmts@cpt.eurofinscn.com

No.331, Guangzhong Road, Zhuanqiao, Minhang
District, Shanghai, China

Website: www.eurofins.cn